MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE Ky. 787 LOT 38282

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
1660	1	T- 249		
1730	1	T- 87		
	STUMP	CUMP 3281		

TOTAL NET WT. 3390 PKG. N–CODE

PROD. SPVR. DATE WHSE. OPER.

12/22/80

N34783

DUP050105272

23
244

CG 03 CODE KY-787-D PKG. ____

→ DEC 16 80 38282

EST. WGT. ~~1000~~ 932 LBS.

OK
AK

3332

PROCESSING INSTRUCTIONS: BATCH UNIT

	PROCESSES	APPROVED BY
	KY-787-D (Q)	EWK 9/22/76
		DCG 9/27/76
	RETYPED BY	
	CJH 4/2/80	

MAKING NOTES

REMARKS

NAME: KROLOR - YELLOW MEDIUM — NON-BLEEDING

INSTRUCTIONS					-PRESSING- RECORD					
VAT	244				PRESSLOAD STARTED	1ST 600	2ND	3RD	4TH	5TH
DATE	12-17-80				CAKES USED	46				
TIME	5:20 Am				WATER ON	10 PM				
RELEASED BY	C.M.				HRS. WASHED	2				
PRESS	22	23	24	25	OHMS	2000				
NO. OF CAKES	46	46	52	48	HRS. WASHED					
PRESS WITH AGITATION					OHMS					
WASH TO 2000 OHMS WITH 35-75 F WATER					HRS. WASHED					
TEST AFTER 2 HOURS					OHMS					
LOAD ON 6 CARS					CAKE CONDITION	-7				
					NO. CARS LOADED					
					EXPLAIN LOSSES					
SAMPLES 1-8 OZ JAR										
DELIVER TO CTL FOR COLOR					SAMPLED BY 201		RELEASED BY AK			

-DRYING-

DRY 12 HRS AT 220 °F	LUMP: - OK - WET - SALTS - CONTAMINATE
THEN DRY 6 HRS AT 160 °F	
	ADDITIONAL DRYING HOURS REQUIRED
	NO. DRUMS 13
SAMPLES	NO. CARS PULLED — LUMP WGT. 3281
DELIVER TO	SAMPLED BY — RELEASED BY BLL

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM	SCREEN RPM
MAX. TEMP. 150 °F	MAX. TEMP. °F
	EXPLAIN LOSSES
SAMPLE AFTER / WITHOUT MIXING	DATE MIXED
SAMPLES 1 ENV & 1 PT. CAN	
DELIVER TO CTL	SAMPLED BY — RELEASED BY

DUP050105273

38282
4100
18

0.00	*
2.60	+
0.14	-
2.78	+
0.14	-
2.81	+
0.14	-
2.89	+
0.14	-
2.76	+
0.14	-
2.80	+
0.14	-
2.69	+
0.14	-
2.83	+
0.14	-
2.71	+
0.14	-
2.78	+
0.14	-
2.73	+
0.14	-
2.62	+
0.14	-
1.63	+
0.14	-
32.81	*

DUP050105274