



JEANNETTE, PA.

MATERIAL SPECIFICATION No. 379

Date June 14, 1963

Sheet 1 No. SHEETS 2

Title: Asbestos Yarn - Waxed

I. Scope: This specification covers a fire retardant product known as single asbestos yarn which is made from rubbed asbestos roving. The finished yarn shall have a waxed surface.

II. Asbestos Content:

Min. - 80%

Max. - 84%

III. Service Temperature: The material supplied to this specification shall be capable of withstanding a maximum temperature of 450°F.


IV. Grade and Sizes: The material shall be ASTM D-299, underwriters grade.

Sizes available shall be between 5 and 18 "cut" inclusive.

V. Standard Specification: All provisions and requirements of ASTM D-299, latest revision, shall apply.

Approved M.H. ArthurApproved J. J. Carran

Approved _____

ET-00366
SC-ETM-3142

-601



JEANNETTE, PA.

MATERIAL SPECIFICATION No. 379

Date June 14, 1963

Sheet 2 No. SHEETS 2


Title: Asbestos Yarn - Waxed

Note: This sheet not to be sent to suppliers.

Approved Source:

Johns Manville Corporation

Note that size (cut) must be specified on the purchase order.
At present our only stock size is 8 cut, but other sizes may be
required for future requirements.



Approved [Signature]
Approved [Signature]
Approved _____

ET-00367

602