

CAREY-CANADIAN MINES, LIMITED

EAST BROUGHTON STATION
QUEBEC, CANADA


Carey

ASBESTOS FIBRE

REPLY TO: P.O. BOX 15095
CINCINNATI 15,
OHIO

Bulletin
No. 143

Asbestos



*CCCL 2-16
PLC 3/1
KZL 2-19
LHR 3/1*

MILITARY SPECIFICATION MIL-C-2908A

CEMENTS, FINISHING, INSULATION

Carey-Canadian Asbestos Short Grade 7M-90 meets MIL-C-2908A Military Specification for Type I Asbestos Finishing Cement.

A recent shipment of 7M-90 Asbestos Shorts tested as follows:

	<u>MIL-C-2908A</u>	<u>7M-90</u>
Asbestos Fibre Content	60 to 85% by weight	70%
Coverage (wet), board feet per 1000 lbs. of dry material	30.0 min.	30.5
Hardness, air dry, penetration	0.40 mm., max.	0.34 mm.
Hardness after 6 hours soaking heat at 300° F., penetration	0.40 mm., max.	0.21 mm.

013523

A H Bagenstose
AHBagenstose/jc
Manager - Sales Engineers

UNR 000039