

PRODUCT NAME = MOLYBDATE ORANGE

CG 01 CODE YE-698-D PKG _____
 LOT F2H38 MAY 28 1982

EST. WT. 5547* LBS.

NON-BLEEDING

4/22/82
 PROCESSES APPROVED BY
 YE-698-D (S) F. POST 10/09/81
 ALTERNATE
 TYPED BY JMH

MAKING NOTES

JOB NAME: 01YE698DPS

INSTRUCTIONS		= PRESSING =		RECORD																		
VAT	DATE	TIME	RELEASED BY	PRESS	NO. OF CAKES	PRESS WITH AGITATION	WASH TO 500 M MHOS WITH 35-75* WATER	TEST AFTER 2 HOURS	LOAD ON 7 CARS	PRESSLOAD	STARTED	CAKES USED	WATER ON	HRS. WASHED	M MHOS	HRS. WASHED	M MHOS	HRS. WASHED	M MHOS	CAKE CONDITION	NO CARS LOADED	EXPLAIN LOSSES
242	6-1-82	4:15 AM	A-G	2	92	93	54	54	54	1530 AM	154	161									1+5+1	

SAMPLES 8 OZ
 DELIVER TO CTL.

SAMPLED BY NP
 RELEASED BY LK

= DRYING =
 (EXTRUDED) DRY 10 HRS AT 240 DEG F
 (NOT EXTRUDED) DRY 10 HRS AT 240 F
 LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

SAMPLE

NO CARS PULLED

NO DRUMS 18
 LUMP WGT 55.82

DELIVER

SAMPLED BY
 RELEASED BY JDS

CO-GROUND PER CTL INSTRUCTIONS
 MILL MIKROATOMIZE SCREEN
 MAX. TEMP DEG F
 SET ROOF BLAST - GATE AT '9' FOR
 HIGH AIR FLOW

GRINDING

RPM SCREEN
 MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE
 SAMPLES 1 ENV IF GROUND SEPARATELY
 DELIVER TO CTL

DATE MIXED

SAMPLED BY
 RELEASED BY

N39439

12

12