GC 01 CODE YE-698-D PKG ____

241 LOT MAY -0-81-E-1498

EST'D WGT 3371 01/48

TOTAL EST'D WGT= LBS (CRT ENTRY)

YE-698-D (R) F. POST 4/14/81
ALTERNATE
TYPED BY JMH

MAKING NOTES _____

JOB NAME: 01YE698DPR

INSTRUCTIONS = PRESSING =					RECORD					
VAT		241			PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE		5/19/81			STARTED	11 AM				
TIME		10:00 AM			CAKES USED	42				
RELEASED BY		CW			WATER ON	2:30 PM				
PRESS	2	91	92	93	HRS. WASHED	2				
NO. OF CAKES	32	42	32	32	OHMS	2000				
PRESS WITH AGITATION					HRS. WASHED					
WASH TO 2000 OHMS 35-74 F WATER					OHMS					
TEST AFTER 2 HOURS					HRS. WASHED					
LOAD ON 4 CARS					OHMS					
					CAKE CONDITION					
					NO CARS LOADED	2+3				
					EXPLAIN LOSSES					
SAMPLES					SAMPLED BY					
DELIVER TO					RELEASED BY	BLL				

= DRYING =

(EXTRUDED) DRY 12 HOURS AT 240 DEG F
(NOT EXTRUDED) DRY 14 HOURS AT 240 F

SAMPLES 1 ENV
DELIVER TO CTL

LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

NO DRUMS 11
LUMP WGT 34.88

NO CARS PULLED
SAMPLED BY
RELEASED BY RH

= GRINDING =

MILL MIKROATOMIZE SCREEN RPM
MAX. TEMP DEG F
SET ROOF BLAST GATE AT "9" FOR HIGH AIR FLOW

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 ENV
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

1498
41
85

PAN WET

3.17 +
0.14 +
3.14 +
0.14 +
3.22 +
0.14 +
3.31 +
0.14 +
3.20 +
0.14 +
3.23 +
0.14 +
3.45 +
0.14 +
3.98 +
0.14 +
3.12 +
0.14 +
2.89 +
0.14 +
31.31 *

1498
41
158

0.00 *

31.31 +
3.03 +
0.12 +
34.22 *

DUP050095907