

PRODUCT NAME = MOLYBDATE ORANGE

NON-BLEEDING

CG 01 CODE YC-010-B PKG

PROCESSES APPROVED BY
YC-010-B (G) F.POST 4/14/81
ALTERNATE
TYPED BY JMH

LOT E1052

OK
AP

EST'D WGT 5632

MAKING NOTES

TOTAL EST'D WGT= LBS (CRT ENTRY)

JOB NAME: 01YC010BPG

INSTRUCTIONS			= PRESSING =	RECORD					
VAT	DATE	TIME		PRESSLOAD	1ST	2ND	3RD	4TH	5TH
RELEASED BY	12/25/81	12:30		STARTED		10PM			
PRESS	2	92	93	CAKES USED		54			
NO. OF CAKES	54	54	54	WATER ON					
PRESS WITH AGITATION				HRS. WASHED		2.00			
WASH TO 2000 OHMS WITH 35-75 F WATER				OHMS					
TEST AFTER 2 HOURS				HRS. WASHED					
LOAD ON 7 CARS				OHMS					
				CAKE CONDITION					
				NO CARS LOADED	4+2				
				EXPLAIN LOSSES					

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: -- OK -- WET -- SALTS -- CONTAMINATED
Color appears dry
Batch released

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO CARS PULLED
SAMPLED BY
RELEASED BY RH

NO DRUMS
LUMP WGT 5763

MILL MIKROATOMIZE SCREEN RPM SCREEN RPM
MAX. TEMP DEG F MAX. TEMP F
SET ROOF BLAST - GATE AT "9" FOR
HIGH AIR FLOW

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES
DELIVER TO CTL

DATE MIXED
SAMPLED BY
RELEASED BY

1052

41

17

0.00 *

3.49 +

0.12 ✓

3.36 +

0.12 ✓

3.15 +

0.12 ✓

3.34 +

0.12 ✓

3.16 +

0.12 ✓

3.19 +

0.12 ✓

3.30 +

0.12 ✓

3.31 +

0.12 ✓

3.44 +

0.12 ✓

3.52 +

0.12 ✓

2.59 +

0.12 ✓

34.53 *

0.00 *

34.53 +

3.25 +

0.14 ✓

3.42 +

0.14 ✓

3.42 +

0.14 ✓

3.31 +

0.14 ✓

3.28 +

0.14 ✓

3.41 +

0.14 ✓

3.45 +

0.14 ✓

57.63 *