GOODS	Endurance Tint Base	LABORATORY NO.	
CONSISTENCY	Liquid	COST CLASS.	DATE 9/4/
FOR USE ON		STRAINER	GRIND 3-4
CUSTOMER		MILL Pebble or	WT. OR BE 13.6#

CODE NUMBER	ONE GALLON BATCH PINTS	LBS.	OZS.	LARGE BATCH GALS.	LBS.	OZS.
W-180		5			350	
W-33		3	11		260	
W-63		2	12		195	
W-195			1		4-1/2	
O-286	1-1/2			13		
O-62	1/4			2-1/4		
O-1	4-1/2			40		
S-43	1-1/2			13		
S-148	1/2			4-1/2		
VM-432		2 Loz.		1-1/8		
VM-523		1 Loz.		1/2		
VM-433		5/16 Loz.			22 Loz.	
S-72		1/2 Loz.			35 Loz.	
APA Advance Puffing Agent if needed.				1/8 or 1/4 Gal. /100 Gals.		
YIELD	1.42			100		

IS AGITATOR ~~REQUIRED~~	Hy-R
VISC. F.B.	85-90 KU TEMP.
VISC. RED.	TEMP.
VISCOSIMETER	Stormer
COLOR	SHEEN
NON VOL.	FLASH PT.
MATCH FOR	
REDUCER	S-43
AMT. FOR BRUSHING	as needed
SPRAYING	TUMBLING
DIPPING	DRIP TIME
BAKE	TEMP.
AIR DRIES IN	O.N.
A. D. TO RECOAT IN	72 hrs.
REMARKS:	
FORMULATOR	J.E. Southwick

Standard Formula
Not to be taken
from File.

28-8-8

N12029

GLD058972

COST	DATE	ANALYSIS		CUSTOMERS Y-1804-U
		PIGMENT 59 %		Endurance Tint Base
		VEHICLE 41 %		9/4/56
		100		N.Y. Trade Sales Inst 9-10-56
				~~Keith Paper~~
		PIGMENT		Keith Paper 9-13-56
		Titanium Calcium	43%	per L.N.
		Zinc Oxide	32	
		Calcium Carbonate	25	
			100%	
		VEHICLE		
		Raw Linseed Oil	55%	
		Bodied Linseed Oil	22	
		Mineral Spirits & Driers	23	
			100%	
		Y-1804	659	

GLD058973