

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE YF-16 LOT 1

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
<u>50</u>	<u>61</u>	<u>3.050</u>		

STUMP

TOTAL NET WT. 3062 PKG. N-CODE 1000

PROD. SPVR. 11/18/81 DATE 11/18/81 WHSE. OPER. 11/18/81

36/841

CG 01 CODE YC-16-B PKG. 93
 MAY -0-81-E-1345
 EST. WGT. 3130 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

(A) YC-16-B	APPROVED BY A.G. 1-1-75
	JFH 5-5-75
	BCG 5-4-75
	TYPED BY

MAKING NOTES

REMARKS

ME: MOLYBDATE ORANGE

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

AT	241						PRESSLOAD	1ST	2ND	3RD	4TH	5TH
ATE	5-16						STARTED	12:30				
ME	945R						CAKES USED	30				
RELEASED BY	UDC						WATER ON	2 AM				
PRESS	91	92	93	2	25		HRS. WASHED	2				
NO. OF CAKES	42	32	32	32	32		OHMS	5500				
PRESS							HRS. WASHED					
ASH TO	2000						OHMS					
EST AFTER	2						HRS. WASHED					
LOAD ON 4 CARS							OHMS					
							CAKE CONDITION	2+3				
							NO. CARS LOADED	2+3				
							EXPLAIN LOSSES					

SAMPLES			
DELIVER TO		SAMPLED BY	RELEASED BY

-DRYING-

DRY	16 HOURS AT	220 F	LUMP: - OK - WET - SALTS - CONTAMINATED
			DRYER SECTIONS USED:
			No record of any processing losses with bleed.
			ADDITIONAL DRYING HOURS REQUIRED
			NO. DRUMS
SAMPLES			NO. CARS PULLED
DELIVER TO			LUMP WGT.
			SAMPLED BY
			RELEASED BY

-GRINDING-

MICROATOMIZE	SCREEN	RPM
SET ROOF GATE AT 5 INCHES AIR FLOW	MAX. TEMP.	° F
MAGNETIC READING ON ARMATURE PANEL 1.0"		
	EXPLAIN LOSSES	
SAMPLE	DATE MIXED	
SAMPLES 1 INV		
DELIVER TO	SAMPLED BY	RELEASED BY
CTL		

1345
41
305

0.00 *

3.00 +
0.12 ✓
2.90 +
0.12 ✓
2.98 +
0.12 ✓
2.94 +
0.12 ✓
0.99 +
0.12 ✓
12.21 *

1345
41
85

3.14 +
0.14 ✓
2.98 +
0.14 ✓
3.16 +
0.14 ✓
2.98 +
0.14 ✓
2.98 +
0.14 ✓
2.96 +
0.14 ✓
1.19 +
0.14 ✓
12.21 +
30.62 *