

The Spectrographic Determination of Pb in Eagle Insulating Wool.

#1 Eagle Loose Insulation

Analysis No.	36A-1392
Sample	1.0 grams
Mgs Pb found	9.6
% Pb	0.96

#2 Eagle Type H-1 (Granulated) Insulation

Analysis No.	36A-1393
Sample	1.0 gram
Mgs Pb found	11.2
% Pb	1.12

Reported: 5-7-1936