

ONE

GALLON

O'BRIEN'S

Flexico

MARINE TYPE SUPER ENAMEL

MILORI GREEN

FOR
INSIDE
OUTSIDE
USE

MANUFACTURED IN U.S.A. BY THE O'BRIEN CORPORATION • SOUTH BEND, INDIANA

REGISTERED
REC'D. No. 95134
DATE 8-10-59

DIRECTIONS FOR USE

OLD PAINTED SURFACES IN GOOD CONDITION
—one or two coats of Flexico.

DRYING—allow overnight drying between coats.
TINTING—Flexico Colors may be tinted with O'Brien's Tone-All Colors.

CAUTION! COMBUSTIBLE

**KEEP AWAY FROM HEAT
AND OPEN FLAME
CONTAINS LEAD OR OTHER COM-**

DO NOT apply on toys, furniture or interior surfaces which might be chewed by children. Use with adequate ventilation. Avoid breathing vapor or spray mist. Avoid prolonged contact with the skin. Wash thoroughly after handling and before eating or smoking. Keep container closed when not in use.

FLEXICO - MILORI GREEN	
Pigment	9.19%
Phthalocyanine Green	20.57%
Titanium Yellow	15.07%
Barium Sulphate	52.14%
Carbon Dioxide	10.83%
C.R. Red Iron Oxide	1.42%
Lemblack	100.00%
Vehicle	90.81%
Modified Sova Alkyd Resin	46.78%
Modified Phenolic Resin	5.69%
China Wood Oil	2.27%
Mineral Salts and Driers	45.26%
	100.00%

THE O'BRIEN CORPORATION

SOUTH BEND, IND. BALTIMORE, MD.
OKLA. CITY, OKLA. SAN FRANCISCO, CAL.
LOS ANGELES, CAL.

ONE

GALLON

O'BRIEN'S

Flexico

MARINE TYPE SUPER ENAMEL

PRIMROSE

FOR
INSIDE
OUTSIDE
USE

MANUFACTURED IN U.S.A. BY THE O'BRIEN CORPORATION • SOUTH BEND, INDIANA

O'BRIEN'S FLEXICO ENAMEL

Made with Alki-therm, Flexico is a deluxe high-gloss enamel which imparts unusual beauty and extra protection to almost any surface. Popular for interior use in kitchens and bathrooms—on walls, trim, cabinets, furniture. Excellent for exterior work—on boats, porch furniture, etc. Its marine type formulation insures a tough, hard finish that's extremely resistant to water, sun, wear and abrasion. Easily applied with brush or spray. Flows on—no brush marks. Dries quickly.

DIRECTIONS FOR USE

NEW WOOD—apply one coat of O'Brien's White Surfacer or Double-Up Undercoat and finish with one or two coats of Flexico. Note—on boats use three thin coats of Flexico only. Thin first coat 10% with turpentine.

NEW PLASTER—apply one coat of O'Brien's Liquid Velvet Wall Primer and Sealer. Finish with one or two coats of Flexico.

NEW METAL—one coat of O'Brien's White Surfacer or Double-Up Undercoat followed with one or two coats of Flexico. Note—Use Tame-Rust Metal Primer on new steel boats. Galvanized or fiber glass boats require special primers and treatment.

OLD PAINTED SURFACES IN GOOD CONDITION—one or two coats of Flexico.

RECEIVED
REC'D. No. 9513A
DATE 8-10-59

GENERAL DIRECTIONS—mix the enamel thoroughly before using and apply with a soft bristle brush. Sand and dust carefully between coats.

SURFACE PREPARATION—surfaces should be clean and dry, free of wax, oil, grease or soap compounds.

THINNING—Flexico is ready for use. If it appears too heavy and easier brushing is desired, thin accordingly with turpentine or O'Brien's Reducit.

DRYING—allow overnight drying between coats.

TINTING—Flexico Colors may be tinted with O'Brien's Tone-All Colors.

CAUTION! COMBUSTIBLE

KEEP AWAY FROM HEAT AND OPEN FLAME. CONTAINS LEAD OR OTHER COMPOUNDS HARMFUL IF EATEN. Do not use on interior surfaces which might be chewed by children. Use with adequate ventilation. Avoid breathing vapors or contact with the skin. Wash thoroughly after handling and before eating or smoking. Keep container closed when not in use.

FLEXICO - PRIMER
Pigment Oxide 17.32%
Hansa Yellow 10.83%
Vulcan 100.00%
Modified Sero Alkyd Resin 44.53%
China Wood Oil 2.40%
Mineral Spirits and Diluents 27.71%
100.00%

THE O'BRIEN CORPORATION

SOUTH BEND, IND. BALTIMORE, MD.
OKLA. CITY, OKLA. SAN FRANCISCO, CAL.
LOS ANGELES, CAL.