

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE KY-781 LOT 33895

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
<u>50</u>	<u>102</u>	<u>5100</u>		

STUMP

TOTAL NET WT. 5100 PKG. N-CODE 10

PROD. SPVR. WK DATE 1/25/80 WHSE. OPER.

S/5 BA98

CG 03 CODE KY-781-D PKG. _____

→ JAN 19 33895

EST. WGT. 1018 1128 LBS.

Impi.
USE A MAGNETIC SEPARATOR IN LINE ^{OK} when pressing this batch, SUSPECT METAL 4468 IN BATCH.

Total Wgt. 4428#

PROCESSING INSTRUCTIONS: BATCH UNIT

22 340	PROCESSES KY-781-D (N)	APPROVED BY: FWP 10-13-78 AMJ 10-13-78
	TYPED BY emw101378	
	MAKING NOTES	
	REMARKS	

NAME: KROLOR® YELLOW LIGHT

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT			243		PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE			1-20-80		STARTED	9:24				
TIME			10:00		CAKES USED	52				
RELEASED BY			K.A.		WATER ON	5:00				
PRESS	2	22	(23)	24	HRS. WASHED	8 HRS				
NO. OF CAKES	46	46	(46)	52	OHMS	5000				
PRESS	with AGITATION				HRS. WASHED					
WASH TO	5000 OHMS with 35-75°F water				OHMS					
TEST AFTER	4 HOURS				HRS. WASHED					
LOAD on 6 cars					OHMS					
					CAKE CONDITION	7				
					NO. CARS LOADED					
					EXPLAIN LOSSES					

SAMPLES 1-8 oz jar
DELIVER TO CTL FOR COLOR

SAMPLED BY HN2 RELEASED BY DR

-DRYING-

DRY	16	HOURS AT	220	°F	LUMP: - OK - WET - SALTS - CONTAMINATED
					color appears dry.
					ADDITIONAL DRYING HOURS REQUIRED
					NO. DRUMS 21
SAMPLES					NO. CARS PULLED
DELIVER TO					LUMP WGT. 4250
					SAMPLED BY
					RELEASED BY

-GRINDING-

MILL 939 HSP	3/32" RP	SCREEN 3500	RPM	SCREEN	RPM
MAX. TEMP.	210°F.			MAX. TEMP.	°F
				EXPLAIN LOSSES	
				DATE MIXED	
SAMPLE WITHOUT MIXING				SAMPLED BY	
SAMPLES 1 Env & 1 Pt Can				RELEASED BY	
DELIVER TO CTL					

DUP050094204

N 26405.01

33895

41

252

0.00 *
2.48 +
0.14 -
2.46 +
0.14 -
2.80 +
0.14 -
2.54 +
0.14 -
2.59 +
0.14 -
2.42 +
0.14 -
2.38 +
0.14 -
2.62 +
0.14 -
2.59 +
0.14 -
2.43 +
0.14 -
2.54 +
0.14 -
2.47 +
0.14 -
2.39 +
0.14 -
2.45 +
0.14 -
2.64 +
0.14 -
2.51 +
0.14 -
2.61 +
0.14 -
2.47 +
0.14 -
2.35 +
0.14 -
2.27 +
0.14 -
0.91 +
0.14 -
47.98 *