

N37358

O.T

122.+
128.+
137.+
135.+
144.+
119.+
128.+
118.+
138.+
129.+
132.+
125.+
126.+
133.+
1814.7

CG 20 CODE BT-297-D PKG.

→ OCT-2-80 37327
EST. WGT. 1931 LBS.

MAKING: Calc. + Fill in Est Wgt.

PROCESSING INSTRUCTIONS: BATCH UNIT

BT-297-D (M)	APPROVED BY AJC 3-11-77
	DCG 3/11/77

TYPED BY	
NE 3/19/77	

MAKING NOTES

REMARKS

NAME: MONASTRAL® BLUE G

NON-BLEEDING

INSTRUCTIONS

- PRESSING -

RECORD

VAT						PRESS/LOAD	1ST	2ND	3RD	4TH	5TH
DATE						STARTED	12A				
TIME						CAKES USED	60				
RELEASED BY						HRS. TO FILL					
PRESS	9+10	15+16	17+18								
NO. OF CAKES	3x76x22	6x42	6x42								
PRESS without		AGITATION									
WASH TO		OHMS									
TEST AFTER		HOURS									
LOAD	on 6 cars for 15/16 & 17/18 PR										
	on 7 cars for 9/10 PR										
						CAKE CONDITION					
						NO. CARS LOADED	7				
						EXPLAIN LOSSES					

**SAMPLES
DELIVER TO**

SAMPLED BY	
------------	--

RELEASED BY 105

4DRYING-

DRY 16 HOURS AT 220°F LUMP: - OK - WET - SALTS - CONTAMINAT

use containers provided

SAMPLES ~~2~~ 1 gallon samples

DELIVER TO

ADDITIONAL DRYING HOURS REQUIRED

No. Drums 73

NO. CARS PULLED
SAMPLED BY

LUMP WGT. 1880
RELEASED BY ac

-GRINDING-

MILL 7 or 8 LSP 3/32" RP SCREEN 1785 RPM
MAX. TEMP. OF

SCREEN	RPM
MAX. TEMP.	°F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING

DATE MIXED 7/2

SAMPLES 1 Env. #2 - 1 Yellow Container
DELIVER TO CTL

SAMPLED BY

RELEASED BY

N37358.01

DUP050041747

37327
51
231

1.66 +
0.14 -
1.67 +
0.14 -
1.62 +
0.14 -
1.71 +
0.14 -
1.74 +
0.14 -
1.70 +
0.14 -
1.62 +
0.14 -
10.74 *
10.74M+

37327
51

69

13
Drums

1.57 +
0.14 -
1.63 +
0.14 -
1.55 +
0.14 -
1.60 +
0.14 -
1.65 +
0.14 -
0.90 +
0.14 -
8.06 *
8.06M+

10.74 +
8.06 +
18.80 *
18.80M+