

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE YT808 LOT 38110

NET WT/PKG NO. PKG PACK. WGT LOCATION PQ

16 2161 36STUMP Lump 2146TOTAL NET WT. 2161 PKG. N-CODE

PROD. SPVR. DATE WHSE. OPER.

WK 12/81 292

N35247

CO 46 CODE YT-808-D PKG.
 → DEC -3 80 38110
 EST. WGT. 2238 LBS.

88"
 142"

920

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
YT-808-D (D)	ENK 9/28/77
	BBK 10/17/77
	DCG 10/17/77
TYPED BY	
JTC 10/26/77	
MAKING NOTES	

REMARKS

AME: DALAMAR® YELLOW

BLEEDING

INSTRUCTIONS					-PRESSING-	RECORD				
AT				106	PRESSLOAD	1ST	2ND	3RD	4TH	5TH
ATE				12-3	STARTED	12:30				
IME				7:10	CAKES USED	6				
RELEASED BY				SL	WATER ON	3:30				
RESS	32	33	35	70	HRS. WASHED	4 1/2				
O. OF CAKES	60	62	60		OHMS	4000				
RESS	WITHOUT AGITATION				HRS. WASHED		Start Squeeze @ 8:40			
ASH TO	4000	OHMS with 35-75°F water				OHMS	Fin. L.O. 2-9:50			
EST AFTER	4	HOURS				HRS. WASHED				
OAD	on 9 cars				OHMS		2 1/2 P.S.I			
					CAKE CONDITION	6				
					NO. CARS LOADED					
					EXPLAIN LOSSES					

AMPLES
 DELIVER TO

SAMPLED BY

RELEASED BY

-DRYING-

DRY 24 HOURS AT 200°F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

AMPLES
 DELIVER TO

NO. CARS PULLED
 SAMPLED BY

NO. DRUMS 17
 LUMP WGT. 2146
 RELEASED BY

-GRINDING-

MILL 4 of 10 HSP 1/8" RBCREEN 3500 RPM
 MAX. TEMP. 190 °F

SCREEN RPM
 MAX. TEMP. °F

EXPLAIN LOSSES

AMPLE WITHOUT MIXING
 AMPLES 1 env + 1 Pint can
 DELIVER TO C T L

DATE MIXED

SAMPLED BY

RELEASED BY

