



Bell Laboratories

600 Mountain Avenue
Murray Hill, New Jersey 07974
Phone (201) 582-3000

April 10, 1979

PLAINTIFF'S EXHIBIT

SWB-97

Norman E. Wood
New York Telephone Company
1095 Avenue of the Americas
Room 2621
New York, New York 10036

Dear Norm:

The two insulation samples you sent from the 10th Floor Frame of the World Trade Towers have been analyzed for asbestos by x-ray diffraction and polarized light microscopy.

Sample #1

This sample was found to contain approximately 3% chrysotile asbestos by both x-ray diffraction and light microscopy. The presence of asbestos was verified by McCrone Associates (see attachment).

Sample #2

This sample was found to consist of gypsum, quartz and anhydrite. In addition, isotropic fibers similar to mineral wool were seen under the optical microscope. No trace of either serpentine or amphibole asbestos was found.

If you have any questions about these samples please give me a call.

Charles P. Lichtenwalner

Att.
Stated Above

Copy to
See next page

CONFIDENTIAL

003570

Mr. N. E. Wood - 2

Copy to

P. H. Stark - NYT

C. H. Steinmetz, M.D.

R. L. Beach - AT&T

N. J. DeCapua

J. M. Degen ✓

R. W. Stone, M.D.

W. J. Schreiber - BTL

G. M. Wilkening

CONFIDENTIAL

003571