

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE

YT 714

LOT

36699

NET WT/PKG

NO. PKG

PACK. WGT

LOCATION

PQ

15

2264

10

STUMP

Lump net 2283

TOTAL NET WT.

2264

PKG. N-CODE

PROD. SPVR

DATE

WHSE. OPER.

JAB

9/11/11

292

D.T.

145.+
 144.+
 166.+
 195.+
 150.+
 140.+
 174.+
 130.+
 151.+
 139.+
 181.+
 150.+
 141.+
 120.+
 138.+
 2264.T

N37542

33/106

JUL 28 1980

CG 50 CODE YT-714-D PKG.

JUL 30 80 36699

EST. WGT. 2224 LBS.

15

2 29

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES
YT-714-D (G)
APPROVED BY
BBK 12-1-77
DCG 12-1-77

TYPED BY
NSA 3-28-78

MAKING NOTES

REMARKS

NAME: GREEN GOLD

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT 106
DATE 7-30-80
TIME 4:55 AM
RELEASED BY E.M.
PRESS 32
NO. OF CAKES 60
PRESS without AGITATION
WASH TO 1500 OHMS with 35-75°F water
TEST AFTER 10 HOURS
LOAD on 7 cars

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	10:40 AM				
CAKES USED	68				
WATER ON	1:50 AM				
HRS. WASHED	30				
OHMS	4000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	7				
EXPLAIN LOSSES					

SAMPLES 4 oz.
DELIVER TO Hold for PE

SAMPLED BY 401 RELEASED BY J.C.

-DRYING-

DRY 22 Hrs at 200°F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 4 oz.
DELIVER TO Hold for PE

NO. CARS PULLED 7
SAMPLED BY
NO. DRUMS 13
LUMP WGT. 2283
RELEASED BY J.C.

-GRINDING-

MILL 8 HSP 1/8" RP SCREEN 3560 RPM
MAX. TEMP. 150°F

SCREEN
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING
SAMPLES 1 Env & 1 Pt Can
DELIVER TO C.T.L.

DATE MIXED 9/11/80
SAMPLED BY 299
RELEASED BY

N37542.01

DUP050045743

36699
54
347

0.00 *

1.70 +

0.14 -

1.86 +

0.14 -

1.59 +

0.14 -

4.73 *

4.73 +

2.00 +

0.14 -

2.05 +

0.14 -

2.05 +

0.14 -

2.05 +

0.14 -

2.05 +

0.14 -

2.12 +

0.14 -

2.08 +

0.14 -

2.00 +

0.14 -

1.95 +

0.14 -

1.15 +

0.14 -

22.83 *