

- 17 -

RECEIVED BY CHIEF OF BUREAU OF WEAPONS, TB
 Proposed by Three Manufacturers in Chicago, January 1941 - June 1942

Embossing FormulaEmbossing Formula

Percentage Formula : Working or Vat Formula

<u>January 1941 to May 1942 2/</u>	<u>Percent</u>	<u>January 1941 to May 1942</u>	<u>Gals.</u>	<u>Lbs.</u>
	35.5	Lithophone		400
	<u>64.5</u>	Wall Special Mixing Varnish	92	
	100.0	Colligen Line Drier	1 1/2	
		Intense Drier	2	

June 1942 2/

June 1942

<u>Percent</u>		<u>Gals.</u>	<u>Lbs.</u>
35.5	Lithophone		400
<u>64.5</u>	Embossing Varnish	92	
100.0	Colligen Line Drier	1 1/2	
	Intense Drier	2	

Red Barn Paint (702)

Percentage Formula : Working or Vat Formula

<u>January 1941 to June 1942 2/</u>	<u>Percent</u>	<u>January 1941 to June 1942</u>	<u>Gals.</u>	<u>Lbs.</u>
	55.3	Venetian Red		250
		Actonite		250
	<u>44.7</u>	Asbestine		200
	100.0	Flown Soya Bean Oil	10	
		Raw Linseed Oil	13	
		Gloss Oil	24	
		Clean Spirits	14	
		Intense Drier	4	
		Solution	1	
		Cobalt Drier	2	

Notes from working formula.