

LOT

K2J40

EST. WT. 4448* LBS.

COMTYP JOB NAME: 01YE721DBM

MAKING NOTES:

= PRESSING =

INSTRUCTIONS

RECORD

VAT 1241
 DATE 10-21-82
 TIME 10:30
 RELEASED BY [Signature]
 PRESS 93 92
 NO. OF CAKES 48 48
 PRESS WITH AGITATION
 WASH TO 500 M MHOS - 35-75% WATER
 TEST AFTER 2 HOURS
 LOAD ON 6 CARS

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	9PM				
CAKES USED	48				
WATER ON	12:30				
HRS. WASHED					
M MHOS					
HRS. WASHED					
M MHOS					
HRS. WASHED					
M MHOS					
CAKE CONDITION	6				
NO CARS LOADED					
EXPLAIN LOSSES					

SAMPLES 8 OZ.
 DELIVER TO CTL

SAMPLED BY [Signature]
 RELEASED BY [Signature]

= DRYING =

EXTRUDED - DRY 10 HRS. AT 240* F
 NOT EXTRUDED - DRY 10 HRS. AT 240* F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
 DELIVER TO

NO CARS PULLED
 SAMPLED BY
 RELEASED BY

NO DRUMS
 LUMP WGT

25
 4627
 [Signature]

= GRINDING =

CO-GROUND PER CTL INSTRUCTIONS
 MILL MIKROATOMIZE SCREEN
 MAX. TEMP DEG F
 SET FLOW AIR GATE AT '5'

RPM

SCREEN
 MAX. TEMP.

RPM
 F

EXPLAIN LOSSES

SAMPLE W/D MIXING
 SAMPLES 1 ENV & 1 PINT CAN IF
 GROUND SEPARATELY
 DELIVER TO CTL

DATE MIXED

SAMPLED BY
 RELEASED BY

40
41
427

0.00 *
3.34 +
0.12 -
3.19 +
0.12 -
3.53 +
0.12 -
3.57 +
0.12 -
3.31 +
0.12 -
3.67 +
0.12 -
3.38 +
0.12 -
3.44 +
0.12 -
3.16 +
0.12 -
1.28 +
0.12 -
30.67 *

40
41
305

0.00 *
30.67 +
3.05 +
0.12 -
3.03 +
0.12 -
3.43 +
0.12 -
3.41 *
0.14 -
3.30 +
0.12 -
46.27 *