VISCOSITY WORK SHEET

Item _____ P.T.No. _____ Date 12-14-54

Worker NH Polymer Butacite Solvent 2-B Alcohol

For Bonetti Charge 1249 Temperature 25°C

Viscometer No. AT Efflux Time .1616 Weight: Gross 6.5306

Viscometer No. BT Efflux Time .1688 Tare 5.4746

Viscometer No. CT Efflux Time .1577 Net 1.0560

331 .1776

Sample	Flask	Visc. No.	Solution Efflux Times	Rel. Visc. or Inh.visc. or M.W.	
11 BAC-33	A	AT	534.7, 535.0, 535.0	86.5	✓
"	M36	BT	517.4, 518.0, 518.1	87.4	
11 BAC-34	M3	CT	512.5, 513.0, 513.0	80.9	✓
"	M25	331	455.4, 455.1, 455.1	80.6	
11 BAC-35	R	AT	600.6, 601.4, 601.5	97.2	✓
"	638	BT	569.4 5705, 570.6	96.3	
11 BAC-36	IJ	CT	564.2, 564.2	88.9	✓
"	1954	331	504.1, 504.1	89.4	
11 BAC-37	M2	AT	639.8, 639.4, 639.3	103.0	✓
"	725	BT	611.8, 612.4, 612.4	103.2	
11 BAC-38	X	CT	572.2, 573.0 572.9	90.2	✓
"	630	331	511.7, 512.2, 512.1	90.8	
11 BAC-39	V	AT	561.8, 562.4, 562.5	90.9	✓
"	K	BT	537.3, 537.8, 537.9	90.8	
11 BAC-40	PRO	CT	565.9, 566.2, 566.2	89.2	✓
"	M8	331	494.0, 494.5, 494.4	87.6	

PC-1

N38690