

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE Ky-787 LOT A2K95

NET WT/PKG NO. PKG PACK. WGT LOCATION PQ

50 62 3100

STUMP 3256

TOTAL NET WT. 3100 PKG. N-CODE 1290

PROD. SPVR. DATE WHSE. OPER.

3/4/71 2/4/71

24
240

DATE PRINTED: 1/06/82

PRODUCT NAME = KROLOR YELLOW MEDIUM

NON-BLEEDING

CG 03 CODE KY-787-D PKG

PROCESSES: APPROVED BY
KY-787-D (R,T) FWP 11/05/81

LOT A2H95

JAN 14 1982

EST. WT. 3394* LBS.

OK/A

TYPED BY JMH
MAKING NOTES

JOB NAME: 03KY787DPT

INSTRUCTIONS

= PRESSING =

RECORD

VAT	DATE	TIME	RELEASED BY	PRESS	NO. OF CAKES	PRESS WITH AGITATION	WASH TO 500 M MHOS WITH 35-75% WATER	TEST AFTER 2 HOURS	LOAD ON 6 CARS	PRESSLOAD	STARTED	CAKES USED	WATER ON	HRS. WASHED	M MHOS	HRS. WASHED	M MHOS	HRS. WASHED	M MHOS	CAKE CONDITION	NO CARS LOADED	EXPLAIN LOSSES	SAMPLED BY	RELEASED BY
1240	1-19-82	1:00 PM	OK	22	46	95/96	24	25	48	1 PM	5:20 PM	52	245 PM	52	52	52	52	52	52	52	6	1" OF COLOR LEFT IN VAT AND PUMPED INTO 2nd PRESS. THE NEXT BATCH TO GO ON TOP OF THIS		

SAMPLES DELIVER TO

= DRYING =

DRY 12 HOURS AT 220* F
THEN DRY 8 HRS AT 160* F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS
LUMP WGT 3256

= CRINDING =

MILL 939HSF 3/32" RP SCREEN 3500 RPM
MAX. TEMP 150 DEG F

SCREEN
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE W/O MIXING 1 ENV & 2 PT CANS
IF PACKED IN BAGS SAMPLE AS FOLLOWS:
FIRST BAG: 1 ENV.
40TH BAG: 1 ENV. & 2 PINT CANS
LAST BAG: 1 ENV.
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

95

51

231

0

295

12

290

12

295

12

280

12

285

12

285

12

280

12

290

12

275

12

275

12

280

12

270

12

3256