MCS 1238 (Sulfone - Hydrocarbon)

Advantages:

Shows good life test results in paper capacitors at G.E. and at other outside labs, and in both paper and polypropylene film capacitors here.

Contains no halogen

Biodegradation 70%

Disadvantages:

Not fire resistant

Cost is greater than ester blends

Assessment:

Probably the best all round non-PCB substiture for Aroclor 1016 except for price.

DSW 283623