



Produced in camera under seal by order of
Judges Paul Riley and Gordon Meag.
October 16, 1989, in Jamison v. A. P. Green
et al. 87-L1230

OC-42-1.



PURCHASE ACCEPTANCE STANDARDS

No. CRM.59.1.465

Date 6/15/62

Supersedes 6/30/61

MATERIAL - Asphalt Roof Coating (Flintkote #214 Semi-Mastic)

SCOPE

This specification covers the necessary data for ordering a fibrated cut-back asphalt used for surface treatment of built-up roofs.

A. DESCRIPTION

Asphalt Roof Coating is a fibrated cut-back of 40 penetration asphalt. It may be applied by brush or spray. This material meets Federal Spec. SSR-451.

B. PROPERTIES

	<u>Rutherford</u>	<u>New Orleans</u>	<u>Chicago Heights</u>
Asphalt %	56.0-62.3	52.8-57.0	64.1-69.3
Asbestos %	8.9-10.1	8.7-9.7	5.3-5.9
Ash %	7.3-8.9	7.2-8.4	4.2-5.2
Volatile %	30.0-32.6	34.4-37.4	26.5-28.9
Weight/Gallon	8.2-8.4	8.0-8.2	7.6-7.8

C. CONTAINER SIZES

1 gallon - 6 per carton
5 gallon container
30 gallon drum
55 gallon drum

D. LABELS

Each container shall be neatly labeled with OCF Label No. L.1.212.

E. WARRANTIES

Manufacturer to warrant material meets these specifications and will replace material not in accordance with specifications.

