

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE

K0-906

LOT

35770

NET WT/PKG

NO. PKG

PACK. WGT

LOCATION

PO

2590

-

1

-

T

-

56

2620

-

1

-

T

-

138

STUMP

TOTAL NET WT.

5210

PKG. N-CODE

PROD. SPVR.

DATE

WHSE. OPER.

JHP

5,23,80

1004001

25
247

MAY 13 1980

CG 04 CODE KO-906-D PKG.
15 35770
EST. WGT. 1377 LBS.

PROCESSING INSTRUCTIONS; BATCH UNIT

PROCESSES	APPROVED BY
KO-906-D (C)	EWK 1/24/78
	DCG 1/26/78
TYPED BY	
rj 3/6/78	

MAKING NOTES

REMARKS

TOTAL WEIGHT 5077# (Req.)

NAME: KROLOR® ORANGE R

NON-BLEEDING

INSTRUCTIONS

- PRESSING -

RECORD

VAT						PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE					5/13/80	STARTED	12:00 PM				
TIME					1:05 AM	CAKES USED	48				
RELEASED BY					OK	WATER ON	5:00				
PRESS	2	22	23	24	25	HRS. WASHED	6				
NO. OF CAKES	46	46	46	52	48	OHMS	2100				
PRESS with						HRS. WASHED					
WASH TO 2000						OHMS					
TEST AFTER 3						HRS. WASHED					
LOAD on 6 cars						OHMS					
						CAKE CONDITION					
						NO. CARS LOADED	5				
						EXPLAIN LOSSES					

SAMPLES 8 oz Jar
DELIVER TO CIL for color

SAMPLED BY 472 RELEASED BY WJ

- DRYING -

DRY	24 HOURS AT	180 °F	LUMP: - OK - WET - SALTS - CONTAMINATED
Dry on first stage only.			
Reset every 5 hrs til dry.			
			ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TONO. CARS PULLED
SAMPLED BYNO. DRUMS 15
LUMP WGT. 5195
RELEASED BY JH

- GRINDING -

MILL 938 HSP 1/8" RP	SCREEN 3500 RPM	SCREEN	RPM
MAX. TEMP. 170 °F		MAX. TEMP.	°F
		EXPLAIN LOSSES	
SAMPLE / WITHOUT MIXING		DATE MIXED	
SAMPLES 1 Env + 1 Pt can			
DELIVER TO CIL		SAMPLED BY RELEASED BY	

DUP050104492

357.70 N C
.41 N
3.24 N
.00 T

3.35 C
.14
3.45
.14
3.31
.14
3.95
.14
3.50
.14
3.57
.14
3.57
.14
3.52
.14
3.67
.14
3.66
.14
3.55
.14
3.91
.14
4 1.33 T

1.58 W C
.00 T

41.33 C
3.58
.12 -
3.60
.12 -
3.80
.12 -
51.95 T