MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE Ky-787 LOT 38.318

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
1612	1	T-35		
1550	1	T-114		
		STUMP Lump .3222		

TOTAL NET WT. 3162 PKG. N–CODE

PROD. SPVR.	DATE	WHSE. OPER.
[illegible]	12/28/80	

N34734

23
240

CG 03 CODE KY-787-D PKG.

→ DEC 18 80 38318

EST. WGT. ~~1090~~ LBS.

OK
HP

3332

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-787-D (Q)	EWK 9/22/76
	DCG 9/27/76
RETYPED BY	
CJH 4/2/80	

MAKING NOTES

REMARKS

NAME: KROLOR - YELLOW MEDIUM

NON-BLEEDING

-PRESSING-

INSTRUCTIONS					
VAT	240				
DATE	12-19-80 (JM)				
TIME	5:30 P.M				
RELEASED BY	E.M.				
PRESS	22	23	24	25	
NO. OF CAKES	46	46	52	48	

PRESS WITH AGITATION

WASH TO 2000 OHMS WITH 35-75 F WATER

TEST AFTER 2 HOURS

LOAD ON 6 CARS

TDS

SAMPLES 1-8 OZ JAR

DELIVER TO CTL FOR COLOR

RECORD					
PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	6 PM				
CAKES USED	52				
WATER ON	130 AM				
HRS. WASHED	6 hr				
OHMS	2000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION	6				
NO. CARS LOADED					

EXPLAIN LOSSES

SAMPLED BY [illegible] RELEASED BY [illegible]

-DRYING-

DRY 12 HRS AT 220 °F

THEN DRY 6 HRS AT 160 °F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 14

SAMPLES

DELIVER TO

NO. CARS PULLED LUMP WGT 3222

SAMPLED BY RELEASED BY [illegible]

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM

MAX. TEMP. 150 °F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE AFTER / WITHOUT MIXING

SAMPLES 1 ENV & 1 PT. CAN

DELIVER TO C T L

DATE MIXED

SAMPLED BY RELEASED BY

DUP050105124

0.00 *

38318
41
188

2.65 +
0.12 -
2.63 +
0.12 -
2.57 +
0.12 -
2.69 +
0.12 -
2.14 +
0.12 -
12.08 *

3 cards

38318
41
58

0.00 *

12.08 +
2.43 +
0.12 -
2.41 +
0.12 -
2.45 +
0.12 -
2.37 +
0.12 -
2.41 +
0.12 -
2.44 +
0.12 -
2.43 +
0.12 -
2.40 +
0.12 -
1.88 +
0.12 -
32.22 *

DUP050105125