

SKIP

V4001 / V4013 5/92

5-13-92 Please mix & Mold Slob of V4001

Caution

Power

& V4013

finished

Pull Tensile

Elong

5-15-92

70.90		04001 - 2											
		5-13-92 CH											
	Code												
Kingl Resin	001	100	00										
Mandel E-68	017	3	00										
Stearic Acid DP	053	0	20										
CS 100-30 Violet	108	0	00										
Synapron 1530	146	2	00										
DINP	006	70	00										
Total	—	175	50										
Duro		64											
Ten		1514											
Elong		423											
Spall		1.161											