11/15/82

PRODUCT NAME: MOLYBDATE ORANGE NON-BLEEDING

CG 01 CODE YC-16-B PKG _____

PROCESSES: YC-16-B (C) APPROVED BY: FWP 09/22/81

LOT L2K64

COMTYP JOB NAME: 01YC016BPC

4038

EST. WT. ~~3098~~* LBS.

MAKING NOTES: _____

INSTRUCTIONS = PRESSING =					RECORD					
VAT	242				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	11-24-82				STARTED					
TIME	2:30p				CAKES USED					
RELEASED BY					WATER ON					
PRESS	1	92	93	2	25	HRS. WASHED					
NO.OF CAKES	42	32	32	32	32	M MHOS					
PRESS WITH AGITATION						HRS. WASHED					
WASH TO 500 M MHOS WITH 35-75* WATER						M MHOS					
TEST AFTER 2 HOURS						HRS. WASHED					
LOAD ON 4 CARS						M MHOS					
						CAKE CONDITION					
						NO CARS LOADED					
						EXPLAIN LOSSES					
SAMPLES						SAMPLED BY					
DELIVER TO						RELEASED BY					

= DRYING =

DRY 16 HOURS AT 220* F	LUMP: - OK - WET - SALTS - CONTAMINATD
	ADDITIONAL DRYING HOURS REQUIRED
	NO DRUMS
SAMPLES	NO CARS PULLED LUMP WGT
DELIVER TO	SAMPLED BY
	RELEASED BY

= GRINDING =

MIKROATOMIZE	SCREEN RPM
SET ROOF GATE AT 2 INCHES AIR FLOW	MAX. TEMP. F
SET LUMP FEED SCREW AT 1/2 SPEED	
MAGNEHELIC READING ON ATOMIZER	
PANEL 1.0"	EXPLAIN LOSSES
SAMPLE WITHOUT MIXING	DATE MIXED
SAMPLES 1 ENV	
DELIVER TO CTL	SAMPLED BY
	RELEASED BY

N40827