

PRODUCT NAME = MOLYBDATE ORANGE

NON-BLEEDING

PROCESSES APPROVED BY
YE-698-D (S) F.POST 4/14/81
ALTERNATE
TYPED BY JMH

MAKING NOTES

JOB NAME: 01YE698DPS

92
245

CE 01 CODE YE-698-D PKG

LOT MAY -0-81-61355

EST'D WGT 5632

TOTAL EST'D WGT= LBS (CRT ENTRY)

INSTRUCTIONS

= PRESSING =

RECORD

VAT
DATE
TIME
RELEASED BY
PRESS 2 92 93
NO. OF CAKES 54 54 54
PRESS WITH AGITATION
WASH TO 2000 OHMS WITH 35-75 F WATER
TEST AFTER 2 HOURS
LOAD ON 7 CARS

1ST	2ND	3RD	4TH	5TH
PRESSLOAD				
STARTED				
CAKES USED				
WATER ON				
HRS. WASHED				
OHMS				
HRS. WASHED				
OHMS				
HRS. WASHED				
OHMS				
CAKE CONDITION				
NO CARS LOADED				
EXPLAIN LOSSES				

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

= DRYING =

(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - DK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 1 ENV
DELIVER TO COLOR TEST LAB

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS
LUMP WGT

= GRINDING =

MILL MIKROATOMIZE SCREEN
MAX. TEMP DEG F
SET ROOF BLAST - GATE AT '9' FOR
HIGH AIR FLOW

RPM SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES
DELIVER TO CTL

DATE MIXED
SAMPLED BY
RELEASED BY

1355
41
231

0.00 *

3.08 +
0.12 ✓
3.25 +
0.12 ✓
3.16 +
0.12 ✓
3.14 +
0.12 ✓
3.44 +
0.12 ✓
3.22 +
0.12 ✓
3.40 +
0.12 ✓
3.48 +
0.12 ✓
3.26 +
0.12 ✓
3.31 +
0.12 ✓
3.43 +
0.12 ✓
3.13 +
0.12 ✓
3.15 +
0.12 ✓
3.13 +
0.12 ✓
3.24 +
0.12 ✓
3.21 +
0.12 ✓
3.40 +
0.12 ✓
3.67 +
0.12 ✓
56.94 *

48
320
9
329