

FORMULA NO. **Y-1804 Emergency**GOODS **Endurance - Tint Base**LASSER **Temporary**CONSISTENCY **Liquid**

COST CLASS.

DATE **7/11/55**

FOR USE ON

STRAINER

GRIND **3-4**

CUSTOMER

MILL **Pebble or** WT. OR BE **13.45**

CODE NUMBER	ONE GALLON BATCH			LARGE BATCH			IS AGITATOR REQUIRED	H. R.
	PINTS	LBS.	OZS.	GALS.	LBS.	OZS.		
W-180		4	12				VISC. F.B. 85-90 KU	TEMP. 74.5
W-33		3	11				VISC. RED.	TEMP. extra
W-63		2	12				VISCOSIMETER Stormer	extra
CH-185			1/2				COLOR White	SHEEN extra
							NON VOL.	FLASH PT.
							MATCH FOR	
0-286	1-1/2						REDUCER S-43	
0-1	3-1/8						AMT. FOR BRUSHING PB	
0-9	1						SPRAYING	TUMBLING
S-43	2-3/8						DIPPING	DRIP TIME
VM-432			2	Loz.			BAKE	TEMP.
VM-433			1/4				AIR DRIES IN O.N.	
* 0-325			2				A. D. TO RECOAT IN 72 hrs.	
* Use only if necessary for body.							REMARKS: Sample of every	
** Use only in absolute emergency when all efforts							batch to be sent to	
to obtain W-170 have been exhausted- Must not be							H. Homana.	
made for stock.								
Approved in emergency per Mr. Mutersbaughs							FORMULATOR H. Homana	
YIELD	1.39 Gal.) (letter of 7/11/55.						PCH 28-8-8	

Standard Formula
Not to be taken
from File.

N12030

GI 0058974

