

NOV 3 1972

W. TOMC
OCT 30 1972

TRADE-MAINTENANCE PRODUCTS

Research Report No. TM-110-A Interim

LEAD REMOVAL - EXTERIOR HOUSE PAINTS

By: Mr. R. H. Ruzicka
Mr. R. W. Green
Mr. J. E. Southwick

Date: October 19, 1972

DPR: 2117-A,C

Distribution: Mr. C. W. Wright - UCB
Dr. H. J. Kiefer - UCB
Mr. G. L. Bechtel - UCB
Mr. H. G. Beck - UCB
Mr. F. G. Hidalgo
Mr. E. B. Euchner
Mr. R. P. Shong
Mr. S. T. Howell
→ Mr. W. M. Tomc
Library
M-E (2)
File

GLD012293

INTRODUCTION

To comply with the Chicago regulation allowing a maximum of .06% lead on the total non-volatile a program was initiated to remove all lead from solvent house paints. For investigative purposes our paints were divided into three groups as follows:

- A. Alkyd house paint - Y-1901
- B. Linseed oil house paints - Y-1801
- C. Exterior wood primer - Y-1851

SUMMARY

1. Manganese in combination with zirconium actually retarded dry as the manganese content increased. This was observed in all 3 systems; Alkyd, Oil, Primer.
2. Manganese in combination with zirconium and cobalt retarded dry as the manganese content increased; all 3 systems.
3. Zirconium gives a tougher through-dry than lead yet the film remains flexible, as tested on the Conical Mandrell; all 3 systems.
4. High cobalt concentrations, up to 0.13% metal for alkyds and 0.125% metal for oil, on vehicle solids, can be used without causing wrinkling if in combination with zirconium.
5. For feeder friers Troykyd Perma-Dry gives a boost to initial dry while Mooney #30 has no effect. Shelf stability is still being investigated.
6. Calcium as a "block" drier, or added to be absorbed by the pigment to prevent drier loss, has no initial effect on dry.
7. In all 3 systems lead-free drier combinations are equal to or better than the standard drier combinations.

Specific recommended drier combinations are as follows:

A. Alkyd House Paints - Y-1901

Standard

<u>Drier</u>	<u>Lbs./100 Gallons</u>	<u>% Metal on Vehicle Solids</u>
E-303	0.50	0.0161 Co
E-325	1.34	0.0323 Mn
E-347	6.43	0.6206 Pb
E-396	4.30	0.5072 Pb feeder

Recommended Lead-Free

E-303	1.00	0.032 Co
E-390	5.00	0.16 Zr
Troykyd		
Perma-Dry	1.50	- - -

Cost increase 2.1¢ per gallon over standard.

Velvet House Paint

<u>Drier</u>	<u>Lbs./100 Gallons</u>	<u>% Metal on Vehicle Solids</u>
E-303	1.00	0.0625 Co
E-347	3.40	0.6375 Pb

Recommended Lead-Free

E-303	1.00	0.0625 Co
E-390	5.00	0.3125 Zr

Cost increase 3.3¢ per gallon over standard.

B. Oil House Paint - Y-1801

Standard

<u>Drier</u>	<u>Lbs./100 Gallons</u>	<u>% Metal on Vehicle Solids</u>
E-325	0.66	0.0155 Mn
E-342	11.60	0.7269 Pb
E-396	5.00	0.5744 Pb feeder
E-382	2.70	0.0423 Ca

Recommended Lead-Free

E-303	3.00	0.0940 Co
E-390	5.00	0.1567 Zr
TroyKyd		
Perma-Dry	1.50	- - - -

Cost increase 3.4¢ per gallon over standard.

C. Exterior Wood Primer - Y-1851

Standard

<u>Drier</u>	<u>Lbs./100 Gallons</u>	<u>% Metal on Vehicle Solids</u>
E-325	1.60	0.0483 Mn
E-347	4.50	0.5436 Pb
E-390	1.50	0.0604 Zr

Recommended Lead-Free

E-303	1.00	0.0403 Co
E-390	5.00	0.2013 Zr
TroyKyd		
Perma-Dry	1.50	- - - -

Cost increase 2.5¢ per gallon over standard.

GLD012296

At 50° F. and 70% R.H. the paints dried considerably slower than at more normal drying conditions; however, the relationships were the same. At 50° F. and 70% R.H. all of the oil house paints wrinkled including the standard, which has no cobalt drier so no special significance could be attributed to the fact that cobalt drier was present in the new recommendations.

These paints will be checked again at 3 to 6 months shelf time to check for loss of dry and/or any change because of the Mooney or TroyKyd feeder driers. Blister resistance tests for Y-1851 are to be completed.

DISCUSSION

Paints were prepared as "blanks", without driers, and then various drier additions were made to carefully weighed samples. These finished samples were then aged for 24 hours and checked for dry, on drawdowns (3 mils wet), on sealed Leneta charts. The drier combinations were tested under both normal exterior summer drying conditions and severe drying conditions in the environmental room.

CODES used in the following detailed listings:

D = Dry Through

TF = Tack Free

S = Soft

M = Mushy

E-303 = Cobalt 12%

E-325 = Manganese 9%

E-347 = Lead 36%

E-396 = Mooney Lead Feeder

E-390 = Zirconium 12%

E-371 = Zinc 16%

E-382 = Calcium 6%

E-342 = Lead 24%

All dry time reported in hours.

a.

DRIER COMBINATION LBS./100 GALLONS

A.

Y-1901	E-303 E-325 E-347 E-396 E-390 E-371 E-382										Troykyd		Mooney	Dry Time Hours	
											Perma-Dry	No. 30		Normal	50°F.- 70 RH
Std.	0.50	1.34	6.43	4.3	-	-	-	-	-	-	-	-	-	Dry	7
Advance	1.88	-	-	-	2.52	-	-	-	-	-	-	-	-	"	7-3/4
Nuodex	0.64	-	-	-	9.52	-	-	-	-	-	-	-	-	"	14
Y-1850	-	1.20	-	-	-	2.20	14.50	-	-	-	-	-	-	"	11-3/4
#1	0.52	1.36	1.60	4.3	3.00	-	-	-	-	-	-	-	-	"	11-1/4
#2	0.52	1.36	-	4.3	3.52	-	-	-	-	-	-	-	-	"	13
#3	0.80	1.36	-	4.3	3.52	-	-	-	-	-	-	-	-	"	17
#4	1.24	-	-	-	2.52	-	-	-	-	-	-	-	-	"	6-1/2
#5	-	3.20	-	-	2.52	-	-	-	-	-	-	-	-	"	12
#6	-	1.60	-	-	2.52	-	-	-	-	-	-	-	-	"	15-1/2
#7	-	1.36	-	-	2.52	2.20	-	-	-	-	-	-	-	"	17
#8	1.88	0.56	-	-	2.52	-	-	-	-	-	-	-	-	"	9
#9	1.88	1.00	-	-	2.52	-	-	-	-	-	-	-	-	"	10-1/2
#10	1.88	1.50	-	-	2.52	-	-	-	-	-	-	-	-	"	11
#11	1.88	1.36	-	4.3	3.52	-	-	-	-	-	-	-	-	"	14-1/2
O-281 Std.	0.50	1.34	6.43	4.3	-	-	-	-	-	-	-	-	-	"	11-1/2
V2393 Std.	0.50	1.34	6.43	4.3	-	-	-	-	-	-	-	-	-	"	8
O-281	1.88	1.50	-	4.3	2.52	-	-	-	-	-	-	-	-	"	11-3/4
V-2393	1.88	1.50	-	4.3	2.52	-	-	-	-	-	-	-	-	"	11
O-281	1.88	-	-	4.3	2.50	-	-	-	-	-	-	-	-	"	9
O-281	1.88	-	-	4.3	1.75	-	-	-	-	-	-	-	-	"	8-1/4
#12	1.88	-	-	-	5.00	-	-	-	-	-	-	-	-	"	8
#13	1.88	-	-	-	2.50	-	-	-	-	-	-	-	-	"	7
#14	1.88	-	-	-	5.00	-	-	-	-	-	-	-	-	"	7-3/4
#15	1.88	-	-	-	5.00	2.20	-	-	-	-	-	-	-	"	5-3/4
#16	1.88	-	-	-	5.00	-	-	-	-	-	1.50	-	-	"	4-1/4
#17	1.88	-	-	-	2.50	-	-	-	-	-	-	-	-	"	6-3/4
#18	1.00	-	-	-	5.00	-	-	-	-	-	1.50	-	-	"	6-1/2
#19	0.50	-	-	-	5.00	-	-	-	-	-	1.50	-	-	"	10
#20	1.88	-	-	-	5.00	-	-	-	-	-	-	4.30	-	"	7-1/4

TF9/Dry O/N
TF14/Dry 24

GLD012299

B.

DRIER COMBINATION LBS./100 GALLONS

b.

Y-1801	E-303		E-325	E-342	E-396	E-390	E-371	E-382	Troykyd		Mooney		Dry Time Hours	
	E-303		E-325	E-342	E-396	E-390	E-371	E-382	Perma-Dry	No.	30	Normal	50° F.	70 RH
Std.	-	2.00	0.66	11.60	5.00	-	-	-	-	-	-	TF9/dry O/N	TF18/dry 24	
2	-	2.00	-	-	-	2.00	-	-	1.50	-	-	TF10-1/2 dry O/N	TF32/dry -	
3	-	2.00	-	-	-	5.00	-	-	1.50	-	-	TF10/dry O/N	TF32/dry -	
4	-	2.00	-	-	-	10.00	-	-	1.50	-	-	TF10/dry O/N	TF18/dry 24	
5	-	3.00	-	-	-	2.00	-	-	1.50	-	-	TF9-1/2/dry O/N	TF17-1/2/dry 24	
6	-	3.00	-	-	-	5.00	-	-	1.50	-	-	TF9/dry O/N	TF17-1/2/dry 24	
7	-	3.00	-	-	-	10.00	-	-	1.50	-	-	TF14-1/2/dry O/N	TF24/dry 48	
8	-	4.00	-	-	-	2.00	-	-	1.50	-	-	TF14-1/2/dry O/N	TF18/dry 24	
9	-	4.00	-	-	-	5.00	-	-	1.50	-	-	TF14/dry O/N	TF18/dry 24	
10	-	4.00	-	-	-	10.00	-	-	1.50	-	-	TF13-1/2/dry O/N	TF18/dry 24	
11	-	2.00	-	-	-	2.00	-	-	-	5.00	-	TF -	TF24/dry -	
12	-	2.00	-	-	-	5.00	-	-	-	5.00	-	TF -	TF24/dry -	
13	-	2.00	-	-	-	10.00	-	-	-	5.00	-	TF22/dry 24	TF18/dry 24	
14	-	3.00	-	-	-	2.00	-	-	-	5.00	-	TF20/dry 24	TF22/dry 26	
15	-	3.00	-	-	-	5.00	-	-	-	5.00	-	TF20/dry -	TF20/dry 30	
16	-	3.00	-	-	-	10.00	-	-	-	5.00	-	TF15/dry O/N	TF21/dry 30	
17	-	4.00	-	-	-	2.00	-	-	-	5.00	-	TF15/dry O/N	TF21/dry 30	
18	-	4.00	-	-	-	5.00	-	-	-	5.00	-	TF14-1/2/dry O/N	TF20/dry 30	
19	-	4.00	-	-	-	10.00	-	-	-	5.00	-	TF14-1/2/dry O/N	TF20/dry 24	
Tenneco 20	0.65	2.10	-	-	-	3.25	-	-	-	-	-	TF15/dry O/N	-	
21	0.65	-	-	-	-	3.25	-	-	-	-	-	TF15/dry O/N	-	
Std.	-	-	0.66	11.60	5.00	-	-	-	-	-	-	TF9/dry 15	-	
Std.	-	-	0.66	11.60	5.00	-	-	-	-	-	-	-	-	
7	-	-	1.20	-	-	5.00	-	-	-	-	-	-	-	
8	-	-	1.40	-	-	5.00	-	-	-	-	-	-	-	
9	-	-	1.60	-	-	5.00	-	-	-	-	-	-	-	
10	-	-	1.40	-	-	5.00	-	-	1.50	-	-	-	-	
Y-2240-F														
Std.	-	-	0.55	7.00	-	-	-	-	-	-	-	TF18/dry 29	TF30/dry 48	
2	-	-	0.55	-	-	7.00	-	-	-	-	-	TF26/dry 33	TF30/dry 48	
3	-	-	0.55	-	-	14.00	-	-	-	-	-	TF27/dry 30	TF30/dry 48	
4	-	-	1.10	-	-	14.00	-	-	-	-	-	TF22/dry 30	TF30/dry 48	

GLD012300

DRIER COMBINATION LBS./100 GALLONS

Y-5003	E-303 E-325 E-342 E-396 E-390 E-371 E-382				Mooney		Dry Time Hours	
	Perme-Dry No. 30				Normal		50° F. - 70 RH	
Std.	-	0.66	11.60	5.00	-	-	/DRY 14-1/2	-
7	-	1.20	-	5.00	-	-	/DRY 20	-
8	-	1.40	-	5.00	-	-	/DRY 22	-
9	-	1.60	-	5.00	-	-	/DRY 22	-
10	-	1.40	-	5.00	-	-	/DRY 19	-
A. Velvet								
Std.	1.00	E-347	-	-	-	-	/DRY 1	TF3/Dry 7
2	1.00	3.40	-	5.00	-	-	/DRY 1	TF3/Dry 6
3	-	2.00	-	5.00	-	-	/DRY 3	TF4/Dry 8
4	-	2.00	-	10.00	-	-	/DRY 6	TF5/Dry 12
C. Primer Y-1851 - No Calcium								
Std.	-	1.60	4.50	-	-	-	TF2/Soft 4	TF11-1/2/S-18
24	0.50	-	-	1.50	-	-	TF2/Dry 7	TF11-1/2/D-19
25	0.50	-	-	5.00	-	-	TF2/Dry 7	TF11-1/2/S-18
26	0.50	-	-	10.00	-	-	TF2/S-7	TF11-1/2/S-18
27	1.00	-	-	2.00	-	-	TF2/D-7	TF11-1/2/D-18
28	1.00	-	-	5.00	-	-	TF2/S-9	TF11-1/2/D-18
29	1.50	-	-	10.00	-	-	TF2/D-6	TF11-1/2/D-18
30	1.50	-	-	2.00	-	-	TF2/S-7	TF11-1/2/D-18
31	1.50	-	-	5.00	-	-	TF2/S-7	TF11-1/2/D-18
32	1.50	-	-	10.00	-	-	TF2/S-7	TF11-1/2/D-15
33	0.50	-	-	2.00	-	-	TF2/S-4	Wet 18 Hrs.
34	0.50	-	-	5.00	-	-	TF2/D-7	Wet 18 Hrs.
35	0.50	-	-	10.00	-	-	TF2/S-7	Wet 18 Hrs.
36	1.00	-	-	2.00	-	-	TF2/S-7	TF11-1/2/S-18
37	1.00	-	-	5.00	-	-	TF2/S-7	TF11-1/2/S-18
38	1.00	-	-	10.00	-	-	TF2/S-7	TF11-1/2/S-18
39	1.50	-	-	2.00	-	-	TF2/S-7	TF11-1/2/S-18
40	1.50	-	-	5.00	-	-	TF2/S-4	TF11-1/2-S-18
41	1.50	-	-	10.00	-	-	TF2/S-7	TF11-1/2-S-18
42	0.50	-	-	2.00	-	-	TF2/S-4	Wet 18 Hrs.
43	0.50	-	-	5.00	-	-	TF2/S-7	Wet 18 Hrs.
44	0.50	-	-	10.00	-	-	TF2/D-7	Wet 18 Hrs.
45	1.00	-	-	2.00	-	-	TF2/D-7	TF11-1/2/S-18
46	1.00	-	-	5.00	-	-	TF2/M-7	Wet 48 Hrs.
47	1.00	-	-	10.00	-	-	TF2/S-7	Wet 48 Hrs.

d.

DRIER COMBINATIONS LBS./100 GALLONS

Y-1851		Troykyd. Mooney										50° F. - 70 RH
No Calcium		E-303	E-325	E-347	E-396	E-390	E-371	E-382	Perma-Dry	No. 30	Normal	
48		1.50	-	-	-	2.00	-	-	-	-	TF2/D-6	TF11-1/2/S-20
49		1.50	-	-	-	5.00	-	-	-	-	TF2/S-7	TF11-1/2/S-20
50		1.50	-	-	-	10.00	-	-	-	-	TF2-1/2/S-7	TF11-1/2/S-18
<u>Y-1851 with Calcium</u>												
Std.		1.00	-	-	-	2.00	-	-	-	-	TF2/D-6	TF6/S-24
19		-	-	-	-	2.00	-	-	-	1.50	TF2/D-5-1/2	TF6/D-O/N
20		0.30	-	-	-	2.00	-	-	-	1.50	TF2/D-6	TF6/D-O/N
21		0.50	-	-	-	2.00	-	-	-	1.50	TF2/D-6	TF6/S-O/N
22		0.70	-	-	-	2.00	-	-	-	1.50	TF2/D-6	TF6/S-O/N
10		1.00	-	-	-	1.00	-	-	-	-	TF2-3/4/D-5	TF9/D-16
11		1.00	-	-	-	2.00	-	-	-	-	TF4/D-6	TF6/D-10
12		1.00	-	-	-	5.00	-	-	-	-	TF-2-1/2/D-4	TF6-1/2/D-9
13		1.00	-	-	-	10.00	-	-	-	-	TF2-1/2/D-4	TF6/D-10
14		1.50	-	-	-	1.00	-	-	-	-	TF2-1/2/D-4	TF6/D-10
15		1.50	-	-	-	2.00	-	-	-	-	TF2-1/2/D3-1/2	TF6/D-10
16		1.50	-	-	-	5.00	-	-	-	-	TF2-1/2/D-4	TF6/D-8
17		1.50	-	-	-	10.00	-	-	-	-	TF2-1/2/D-3	TF6/D-10
Std.		-	1.60	4.50	-	1.50	-	-	-	-	TF4-1/2/D-6-1/2	TF9/D-16
A2		-	1.60	-	-	6.00	-	-	-	-	D-6-1/2	Wet 24
A3		-	1.60	-	-	10.00	-	-	-	-	D-6	Wet
A4		-	1.60	-	-	15.00	-	-	-	-	D-5-1/2	Wet
A5		0.51	-	Act-8	-	-	-	-	-	-	D-4	TF8/D-O/N
A6		0.51	-	-0.62	-	1.02	-	-	-	-	D-4-1/2	TF9/D-O/N
A7		0.51	-	-	-	2.00	-	-	-	-	TF4/D-6-1/2	TF9/D-O/N
A8		0.50	-	-	-	5.00	-	-	-	-	TF4/D-6	TF9/D-O/N
A9		0.50	-	-	-	10.00	-	-	-	-	TF4-1/2/D-71	TF9/D-O/N

GLD012302

COMMENT

Most of the drier recommendations made in this report are in line with the supplier's recommendations with exception of the linseed oil house paint, Y-1801. The .09% cobalt is excessively high in relation to the recommended amounts of .02 to .04%. The reason for this high amount was to achieve equal dry to the standard lead combination under cold damp drying conditions in the environmental chamber. We have been told that cobalt drier in excess of .04% will cause premature cracking and checking. Our own exposure reports of 1952 to 1956 show bad cracking when cobalt drier was used in Y-1850. (House paint - fume resistant.) We do not recommend issuing Y-1801 with .09% cobalt without adequate exposure history. If we had to issue a lead-free formula today we would go with a drier combination that would be 2 hours slower than standard under normal drying conditions and 6 hours slower under cold damp drying conditions.

These drier studies for Y-1801 were done on the 100% oil formula. Future work will be done with the C-pigment replacement formula vehicle system which replaces O-131 bodied linseed oil with alkyd resin V-2385. It is hoped that the dry improvement will be sufficient so the cobalt metal levels can be reduced to a safer level and prevent possible cracking.

FROM : H. D. Swafford

DATE: May 15, 1972

FOR: F. G. Hidalgo

CITY : Coatings & Resins Research Center
Strongsville, Ohio

SUBJECT: TRACE HEAVY METALS IN GLIDDEN PRODUCTS -
INTERIM REPORT

W. TOMC

MAY 25 1972

cc: R. Shong
E. B. Euchner
H. J. Kiefer (UCB)
T. Walsh (UCB)
S. T. Howell
J. Southwick
J. Patrick
G. Proffitt
J. Tapa

pc. WT
GFP

Some time back, 1-gallon quantities of eight (8) high-volume Glidden products were obtained with the goal of analyzing them for a number of trace heavy metals. This report summarizes the findings relative to the lead and cadmium contents of the 8 products.

A modified nitric acid - perchloric acid wet digestion method was used to achieve sample dissolution, followed by atomic absorption analysis for the two elements. The following results were obtained:

<u>SAMPLE</u>	<u>T.H.V.</u>	<u>LEAD (On Solids)</u>	<u>CADMIUM (On Solids)</u>
Y-3418	49.8%	15.5 P.P.M.	7.0 P.P.M.
Y-3454	49.9%	32.3 P.P.M.	3.8 P.P.M.
Y-3600	57.3%	0.21%	35.1 P.P.M.
Y-4600	65.6%	0.46%	2.4 P.P.M.
Y-917	49.3%	0.29%	3.0 P.P.M.
Y-3608	53.8%	0.12%	3.9 P.P.M.
Y-1828	66.0%	1.36% *	2.9 P.P.M.
Y-1801	84.1%	0.41%	0.7 P.P.M.

* This exceeds the amount that should be present, so the analysis was repeated, with similar results being obtained. The pigments (plus Nuact paste) were then removed by centrifugation and lead was determined on the clear vehicle. A value of 0.12% lead was obtained on the vehicle, which calculates to 0.15% of the paint solids. The balance (1.21%) was removed by the centrifuging process (Nuact paste?).

Analyses for the other trace heavy metals in these paints will proceed as time permits (to experimentally devise and evaluate the analytical techniques needed for each element).

hga

H. D. Swafford

GLD012304