



Soma Peppe-DRA

800-149-2A

INTERNAL CORRESPONDENCE

CHEMICALS AND PLASTICS

120 SOUTH RIVERSIDE PLAZA • CHICAGO, ILLINOIS 60606

To (Name) F. W. Ducca

Date December 21, 1971

Company

Originating Dept. Thermosetting Resins and Compounds

Location Bound Brook

Answering letter date

Copy to

C. F. Martino-Bound Brook
P. B. Potter-New York (32)
B. Letizia-Chicago

Subject CUTLER HAMMER
LINCOLN, ILLINOIS

The following is a listing of the box test results of BMMB 5020 BK 25 GR 9, Blends 577 and 579 that were sent to Cutler Hammer for approval:

<u>Pressure</u> <u>P.S.I.</u>	<u>Blend</u> <u>577</u>	<u>Blend</u> <u>579</u>
3500	9.5	8.5
3000	10.2	9.0
2500	12.5	11.2
2000	16.0	15.5
1500	26.2	22.7
1000	<u>34.0</u>	<u>31.2</u>
	108.4	98.1

Blend 577 has been rejected because it is over our maximum of 105. Blend 579 has been approved and will be allocated and shipped against open orders.

George T. Cassidy
George T. Cassidy

GTC:dlh

Disposition B#577

UCASB00951117