

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE

Ky. 787

LOT

37763

NET WT/PKG

NO. PKG

PACK. WGT**LOCATION**

PQ

1980

/

7-190

2000

/

T-159

2028

/

T- 66

[REDACTED]

LUMP

6074

TOTAL NET WT.

6,000

PKG. N-CODE

PROD. SPVR.

DATE _____

WHSE. OPER.

11 77

N34847

95
846

NOV 4 1980

CO 03 CODE KY-787-D PKO.

NOV 10 80 37763
EST. WGT. 4921 LBS.

012
FP

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES
KY-787-D (S)
Alternate
APPROVED BY
OK 10-19-77
DCG 10-25-77

TYPED BY
JIC 11-4-77

MAKING NOTES

REMARKS

TOTAL WGT 5845# (REQ)

NAME: KNOLCO YELLOW-MEDIUM

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE			11-17-80		STARTED	3:20				
TIME			10:30		CAKES USED	72				
RELEASED BY			93		WATER ON	12:00				
PRESS	98	96	93		HRS. WASHED	6:15				
NO. OF CAKES	70	72	72		OHMS	3600				
PRESS WITH					HRS. WASHED					
WASH TO	2000				OHMS					
TEST AFTER	4				HRS. WASHED					
LOAD ON TO CARS					OHMS					
					CAKE CONDITION					
					NO. CARS LOADED	10				
					EXPLAIN LOSSES					

7DS

SAMPLES 1-8 oz. JAR
DELIVER TO CTI FOR COLOR

SAMPLED BY RELEASED BY 7DS

-DRYING-

DRY 12 HRS AT 2200F.
THEN DRY 8 HRS AT 1600F

LUMP: - OK - WET - SALTS - CONTAMINATED

Color appears dry
Released batch
ADDITIONAL DRYING HOURS REQUIRED

No. Drums: 26
NO. CARS PULLED 10
LUMP WGT. 6074
SAMPLED BY RELEASED BY OC

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150°F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 env + 1 Pt Can
DELIVER TO C T L

DATE MIXED
SAMPLED BY RELEASED BY

93/246

CO 03 CODE KY-787-D PKG.

NOV 10 80 37763
EST. WGT. 4921 LBS.

012
FP

PROCESSING INSTRUCTIONS

PROCESSES
KY-787-D (S)
Alternate

APPROVED BY
OK 10-19-77
DCG 10-25-77

TYPED BY
JIC 11-4-77

MAKING NOTES

REMARKS

TOTAL WGT 5845# (REQ)

NAME: KNOLCO YELLOW-MEDIUM

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT			246			PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE			11-17-80			STARTED	3:20				
TIME			10:30			CAKES USED	7A				
RELEASED BY			(93)			WATER ON	12:00				
PRESS	98	96	93			HRS. WASHED	6:11				
NO. OF CAKES	70	72	72			OHMS	3000				
PRESS WITH						HRS. WASHED					
WASH TO	2000					OHMS					
TEST AFTER	4					HRS. WASHED					
LOAD ON TO CARS						OHMS					
						CAKE CONDITION					
						NO. CARS LOADED	10				
						EXPLAIN LOSSES					

703

SAMPLES 1-8 GZ. JAR
DELIVER TO C.T. FOR COLOR

SAMPLED BY

RELEASED BY 703

-DRYING-

DRY 12 HRS AT 2200F.
TEMP. THEN DRY 8 HRS AT 1600F

LUMP: - OK - WET - SALTS - CONTAMINATED

Color appears dry
Released batch
ADDITIONAL DRYING HOURS REQUIRED

NO. CARS PULLED 10
SAMPLED BY
No. Drums: 26
LUMP WGT. 6074
RELEASED BY 02

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150°F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE A. WITHOUT MIXING
SAMPLES 1 env + 1 Pz Can
DELIVER TO C.T.

DATE MIXED

SAMPLED BY

RELEASED BY

93
246

CG 03 CODE KY-787-D PKO.

NOV 10 80 37763
EST. WGT. 4921 LBS.

012
FP

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES
KY-787-D (S)
APPROVED BY
ENK 10-19-77
Alternate DCG 10-25-77

TYPED BY
JLC 11-4-77

MAKING NOTES

REMARKS

TOTAL WGT 5845# (REQ 6121#)

NAME: KROLOR® YELLOW-MEDIUM

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT			246			PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE			11-12-80			STARTED	3:00				
TIME			10:30 P			CAKES USED	72				
RELEASED BY			(93)			WATER ON	12:00				
PRESS	98	96				HRS. WASHED	6:11				
NO. OF CAKES	70	72	72			OHMS	3000				
PRESS WITH			AGITATION			HRS. WASHED					
WASH TO	2000		OHMS WITH 35-75°F WATER			OHMS					
TEST AFTER	4		HOURS			HRS. WASHED					
LOAD ON 10 CARS						OHMS					
						CAKE CONDITION					
						NO. CARS LOADED	10				
						EXPLAIN LOSSES					

703

SAMPLES 1-8 oz. JAR
DELIVER TO CTL FOR COLOR

SAMPLED BY RELEASED BY 703

-DRYING-

DRY 12 HRS AT 220°F.
THEN DRY 8 HRS AT 160°F

LUMP: - OK - WET - SALTS - CONTAMINATED

Color appears dry
Released batch
ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

No. Drums: 26
NO. CARS PULLED 10
LUMP WGT. 6074
SAMPLED BY RELEASED BY 02

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150°F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 env + 1 Pt Can
DELIVER TO CTL

DATE MIXED
SAMPLED BY RELEASED BY

229

229

26 drums