

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE

Rt 761

LOT

38-225

NET WT/PKG

NO. PKG

PACK. WGT

LOCATION

PD

12

1843

37

STUMP

LUMP 1822

TOTAL NET WT.

1843

PKG. N-CODE

PROD. SPVR.

DATE

WHSE. OPER.

Rt

12-28-60

L-3

N35071

DUP050107504

[illegible]

37
903

CG 32 CODE RT-761-D PKG.
→ ~~80~~ 80 38215 DEC 16
EST. WGT. 1921 2004 LBS.

9728

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
RT-761-D (K)	JJG 4-4-78
	DCG 4-11-7
TYPED BY	
NSA 4-17-78	
MAKING NOTES	

REMARKS

NAME: WATCHUNG® RED B

NON-BLEEDING

INSTRUCTIONS				-PRESSING-		RECORD				
VAT	703			PRESSLOAD	1ST	2ND	3RD	4TH	5T	
DATE	12/18/80			STARTED	12:30 PM					
TIME	10:30 P			CAKES USED	100					
RELEASED BY	92			WATER ON						
PRESS	32	37		HRS. WASHED	1/2					
NO. OF CAKES	60	60		OHMS	4/500					
PRESS without	AGITATION			HRS. WASHED						
WASH TO 3000	OHMS with 35-75°F water			OHMS						
TEST AFTER 3	HOURS			HRS. WASHED						
LOAD on 7 cars				OHMS						
Press immediately code				CAKE CONDITION						
Instruct Making Area to add 10# N-588-A				NO. CARS LOADED	473					
halfway thru pressing				EXPLAIN LOSSES						
Clean magnetic separator after pressing										
Cleaned by	Time Cleaned									

SAMPLES

DELIVER TO

SAMPLED BY

RELEASED BY

-DRYING-

DRY 20 Hours at 220°F
Hold on track 30 min before dumping pans

LUMP: - OK - WET - SALTS - CONTAMINA

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES

DELIVER TO

NO. CARS PULLED

SAMPLED BY

NO. DRUMS 10

LUMP WGT. 1822

RELEASED BY 130

-GRINDING-

MILL 2 LSP 1/8" RP SCREEN 1750 RPM
MAX. TEMP. 150°F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING
SAMPLES 2 Env. & 2 Pt. Cans
DELIVER TO CTL

DATE MIXED

SAMPLED BY

RELEASED BY

38215
51
16

0.00 *

2.08 +
0.14 -
2.09 +
0.14 -
1.95 +
0.14 -
1.98 +
0.14 -
1.85 +
0.14 -
9.25 *

38215
51
58

0.00 *

9.25 +
2.06 +
0.14 -
2.03 +
0.14 -
1.96 +
0.14 -
1.97 +
0.14 -
1.65 +
0.14 -
18.22 *