

22/243
CG 03 CODE KY-787-D PKG. _____
→ DEC 11-80 38206
EST. WGT. 1000 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES KY-787-D (Q)	APPROVED BY EWK 9/22/76 DCG 9/27/76
RETYPED BY CJH 4/2/80	
MAKING NOTES	

REMARKS

NAME: KROLOR - YELLOW MEDIUM

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT	243					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	12-13-80					STARTED	8:45 AM				
TIME	3:00 PM					CAKES USED	46				
RELEASED BY	5001					WATER ON	2:45 PM				
PRESS	22	23	24	25		HRS. WASHED	3:50				
NO. OF CAKES	46	46	52	48		OHMS					
PRESS WITH						HRS. WASHED					
WASH TO 2000						OHMS					
TEST AFTER 2						HRS. WASHED					
LOAD ON 6 CARS						OHMS					
						CAKE CONDITION	5				
						NO. CARS LOADED					
						EXPLAIN LOSSES					

SAMPLES 1-8 OZ JAR
DELIVER TO CTL FOR COLOR

SAMPLED BY

RELEASED BY

-DRYING-

DRY 12 HRS AT 220 °F
THEN DRY 6 HRS AT 160 °F

LUMP: - OK - WET - SALTS - CONTAMINATED

No record of any losses up
Processing / Release 12-12-80

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TONO. CARS PULLED
SAMPLED BYNO. DRUMS 12
LUMP WGT. 320.2
RELEASED BY AC.

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150 °FSCREEN
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE AFTER / WITHOUT MIXING
SAMPLES 1 ENV & 1 PT. CAN
DELIVER TO CTL

DATE MIXED

SAMPLED BY

RELEASED BY

DUP050105316

38206
41
16

0.00 *

2.76 +

0.12 -

2.87 +

0.12 -

2.74 +

0.12 -

2.61 +

0.12 -

3.04 +

0.12 -

2.88 +

0.12 -

2.87 +

0.12 -

2.71 +

0.12 -

2.66 +

0.12 -

2.94 +

0.12 -

3.07 +

0.12 -

2.31 +

0.12 -

32.02 *