MD-3-A

**PACKAGE TICKET** (DRY AND PASTE ONLY)

CODE B4 384-D LOT E-1576

| NET WT/PKG | NO. PKG | PACK. WGT | LOCATION | PO |
|---|---|---|---|---|
| | 12 | 2221 | 54 | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | STUMP | LW 2227 | | |

TOTAL NET WT. 2221 PKG. N–CODE

| PROD. SPVR. | DATE | WHSE. OPER. |
|---|---|---|
| RP | 3-12-81 | 383 |

```
C
179.+
181.+
178.+
134.+
186.+
192.+
193.+
138.+
196.+
196.+
188.+
130.+
2231.T
C
```

FINISHING Note: Co-PULY WITH N-65-A & MFS

DRS / GBLDG

CG 20 CODE BT-284D PKG. ____

→ E 1579

EST. WGT. 2254 LBS.

MFS

PROCESSING INSTRUCTIONS: BATCH UNIT

| PROCESSES | APPROVED BY |
|---|---|
| | |
| | |
| | |
| TYPED BY | |
| | |

MAKING NOTES

REMARKS

NAME: MONASTRAL & BLUE B

NON-BLEEDING

-PRESSING-

INSTRUCTIONS

| | | | | | |
|---|---|---|---|---|---|
| VAT | | | | | |
| DATE | | | | | |
| TIME | | | | | |
| RELEASED BY | | | | | |
| PRESS | | | | | |
| NO. OF CAKES | | | | | |

PRESS AGITATION

WASH TO OHMS

TEST AFTER HOURS

LOAD PANLOAD

SAMPLES

DELIVER TO

RECORD

| PRESSLOAD | 1ST | 2ND | 3RD | 4TH | 5TH |
|---|---|---|---|---|---|
| STARTED | | | | | |
| CAKES USED | | | | | |
| WATER ON | | | | | |
| HRS. WASHED | | | | | |
| OHMS | | | | | |
| HRS. WASHED | | | | | |
| OHMS | | | | | |
| HRS. WASHED | | | | | |
| OHMS | | | | | |
| CAKE CONDITION | | | | | |
| NO. CARS LOADED | 3+1 | | | | |

EXPLAIN LOSSES

SAMPLED BY RELEASED BY BHe

-DRYING-

HOURS L.V. H.V.

TEMP. °F °F

DRY 20 HRS AT 220°F

LUMP: - OK - WET - SALTS - CONTAMINATE

No record of any processing Losses Can not account for Low yield

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES

DELIVER TO

NO. CARS PULLED

SAMPLED BY

Drums - 12

LUMP WGT. 2077

RELEASED BY RH

-GRINDING-

MILL 7 OR 8 LSP 3/32 HPP SCREEN 1785 RPM

MAX. TEMP. 150 °F

CO-PULY WITH 150 # N-65-A

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE AFTER / [redacted] MIXING

SAMPLE 2 NV + 2 PINTS

DATE MIXED 5/29/81

DUP050097363

CG 20 CODE BT-284-D PKG.

→ MAY 26 (58)

**E1579**

EST. WGT. _____ LBS.

NOTE: MAKING — FILL IN EST WGT FROM BATCH CARD

PROCESSING INSTRUCTIONS: BATCH UN

| PROCESSES | APPROVED |
|---|---|
| BT-284-D (P | AJC 05 10 7 |
| | DCG 07 12 7 |
| | |
| | |
| TYPED BY | |
| emw070279 | |

MAKING NOTES

REMARKS

NAME. MONASTRAL® BLUE B — NON-BLEEDING

## INSTRUCTIONS — PRESSING — RECORD

| | | | | |
|---|---|---|---|---|
| CAT | | | | |
| DATE | | | | |
| TIME | | | | |
| RELEASED BY | | | | |
| PRESS | 9 + 10 | 17 + 18 | | |
| NO. OF CAKES | 2 x 119 + 43 | 3 x 84 + 28 | | |

PRESS with AGITATION

WASH TO _____ OHMS

TEST AFTER _____ HOURS

LOAD on 8 cars

SAMPLES

DELIVER TO

| PRESSLOAD | 1ST | 2ND | 3RD | 4TH | 5 |
|---|---|---|---|---|---|
| STARTED | | | | | |
| CAKES USED | | | | | |
| HRS TO FILL | | | | | |
| CAKE CONDITION | | | | | |
| NO. CARS LOADED | | | | | |

EXPLAIN LOSSES

SAMPLED BY RELEASED BY

## -DRYING-

Dry 18 hrs at 220°F

LUMP: - OK - WET - SALTS - CONTAMINA

ADDITIONAL DRYING HOURS REQUIRED

NO DRUMS

SAMPLES

DELIVER TO

NO. CARS PULLED LUMP WGT.

SAMPLED BY RELEASED BY

## -GRINDING-

MILL 7 or 8 LSP 3/32" RP SCREEN 1785 RPM

MAX. TEMP. 200 °F

SAMPLE WITHOUT MIXING

SAMPLES 1 Env & 1 Pt Can

DELIVER TO C T L

| SCREEN | RPM |
|---|---|
| MAX. TEMP. | °F |

EXPLAIN LOSSES

DATE MIXED

SAMPLED BY RELEASED BY

DUP050097364

1579
51
16

0.00 *

14.36 +
1.94 +
0.14 −
1.97 +
0.14 −
1.87 +
0.14 −
1.19 +
0.14 −
20.77 *

1579
51
17

0.00 *

1.90 +
0.14 −
1.94 +
0.14 −
1.91 +
0.14 −
1.88 +
0.14 −
2.02 +
0.14 −
1.88 +
0.14 −
1.93 +
0.14 −
2.02 +
0.14 −
14.36 *

DUP050097365