

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE Ky 775-L LOT 37473

NET WT/PKG NO. PKG PACK. WGT LOCATION PQ

1 2100 T-3271 2088 T-22STUMP 425TOTAL NET WT. 4188 PKG. N-CODEPROD. SPVR. RH DATE 10/28/80 WHSE. OPER.

N34877

22
240

CO 03 CODE KY-795-D PKG.

OCT-16 80 37473

EST. WGT. 1198 LBS.

012
R

PROCESSING INSTRUCTIONS: BATCH UN

PROCESSES	APPROVED
KY-795-D	EWK 10/6
	DCG 10/7
TYPED BY	

MAKING NOTES

REMARKS

TOTAL WGT. 4878# 4630# 4380

NAME: "KROLOR" YELLOW-MEDIUM

NON-BLEEDING

INSTRUCTIONS					-PRESSING-		RECORD				
AT	240				PRESSLOAD		1ST	2ND	3RD	4TH	5
ATE	10.17.80				STARTED		92				
IME	12.30 PM				CAKES USED		54				
RELEASED BY	(A. G.)				WATER ON		2.0A				
RESS	22	23	24	25	HRS. WASHED		7 1/2				
O. OF CAKES	46	46	52	48	OHMS		5000				
RESS with	AGITATION					HRS. WASHED					
ASH TO	5000	OHMS									
EST AFTER	5	HOURS with 35-75 water					HRS. WASHED				
OAD	on 5 cars						OHMS				
							CAKE CONDITION				
							NO. CARS LOADED	4			
							EXPLAIN LOSSES				

SAMPLES 1-8 oz jar
DELIVER TO CTL for color
SAMPLED BY #469
RELEASED BY A. G.

-DRYING-

Dry 14 Hrs. at 220 F	LUMP: - OK - WET - SALTS - CONTAMINA
NOTE: If dried in 12-23, 80-97, or 138-165 sections; dry for 14 hrs at 220 F record sections; fill in additional hrs required if any:	ADDITIONAL DRYING HOURS REQUIRED
SAMPLES	NO. DRUMS 12
DELIVER TO	NO. CARS PULLED
	SAMPLED BY
	LUMP WGT. 4255
	RELEASED BY A. G.

-GRINDING-

ILL 939 HSP 3/32" RP SCREEN 3500 RPM	SCREEN	RPM
MAX. TEMP. 210°F	MAX. TEMP.	°F
	EXPLAIN LOSSES	
SAMPLE AFTER / WITHOUT MIXING	DATE MIXED	
SAMPLES 1 ENV & 1 Pt Can.	SAMPLED BY	RELEASED BY
DELIVER TO CTL		

0.00 *

37473

41

188

3.85 +

0.12 -

3.60 +

0.12 -

3.96 +

0.12 -

3.35 +

0.12 -

3.77 +

0.12 -

3.50 +

0.12 -

4.01 +

0.12 -

3.90 +

0.12 -

3.55 +

0.12 -

3.55 +

0.12 -

3.80 +

0.12 -

3.15 +

0.12 -

42.55 *

42.55M+

*12
draws*