

Sub GP
Under

Rec D 2

GEORGIA-PACIFIC

INTERDEPARTMENTAL COMMUNICATION

DATE: September 21, 1971

TO: Mr. J. B. Moss

LOCATION: Tigard

FROM: L. E. Winter

LOCATION: Acme

SUBJECT: Supplement to Correspondence Dated August 31, 1971
Comparison of All Purpose Compounds

PLAINTIFF'S EXHIBIT

GP-774

PACO

WC	62
PH	9.0
Bond	100%
Workability	Good
Shear	OK
Shrinkage	Poor
Edge Crack	Good
Wedge Crack	Fair
Hardness	OK
Adhesive	Starch -
Viscosity	500
Working Time	20 min.

RECEIVED

SEP 24 1971

TECHNICAL DEPARTMENT

We rated the Paco the same as U.S.G., which was No. 5 on the comparison conducted August 31, 1971.

L. E. W.

LEW

LEW/om

cc: Messrs. T. W. Richards
C. W. Lehnert
D. C. Corkill
W. N. Gettel
K. W. Brown
D. M. Watson
E. E. Schram

THIS COPY FOR

SGP 0015864