FORMULA RECORD NEWARK ONLY

Exp.No. ____ Date 3-28-35 Rex. No. 354

Name S. W. P. # 354 Sea Green Card No. 9 N See No. 8

650	LBS.	1526	
100	"	20 L	
4	"	98	
2 1/4	"	10617 or 2# 12 07	
	"		
	"		
	"		
	"		
11	GALS.	(2)	
5	"	(213)	
	"	( )	
255 LBS	"	( )	BW 104
52	GLS	(2)	
1/2	"	(12 W)	
3 1/2	"	(2241)	
4 1/2	"	(348)	X
1/8 X	"	(152)	X

Customer S. W. Co.

To Match Std.

Weight Per Gal. T 15.60 Visc.

☐ Red ☒ No Label Required

Baume Std. of Fineness 2 P

40 [illegible] Gals. per hour 30" Mill

New Std. Sample Required No Date Rec'd

Reason for Revision To reduce amount of crystal-lization in warm climates per G. L. Hehl's instructions.

Normal Output 100 Approved Formulator

Est. Mfg. Loss 2% Supt. H V S

Department

Label Analysis Checked - Date A135 Buff

0007-SWP-063062

MANUFACTURING INSTRUCTIONS:

Reduction: Amount Reducer Used

Application: Surface Bldgs. Method Brush

No. Coats Good Two Undercoater Used Primer for new work

Drying Time: Touch 10 Hrs. Handle Recoat 4-5 Days

Rub Sand Wrap Stencil

Baking Time and Temp.

Gloss Oil Film Tough & Hard

Special Tests

PRODUCTION

Date	Slip No.	Amount

FACTORY	FORMULA	SPEC. CARD	STD. SAMPLE	FACTORY	FORMULA	SPEC. CARD	STD. SAMPLE
CLEVELAND				ALLIED RESEARCH			
NEWARK	7-1-35			GIBBSBORO			
KENSINGTON				DAYTON			
OAKLAND				DETROIT			
DALLAS				LONDON			