

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE KY-907 LOT 35178

NET WT/PKG NO. PKG PACK. WGT LOCATION PQ

1780 - 1 - T - 2461630 - 1 - T - 77 STUMP 3380TOTAL NET WT. 3410 PKG. N-CODE PROD. SPVR. DATE 4,8,80 WHSE. OPER.

N32478

95
262

Totes

CA 03 CODE KY-907-D PKG. _____
 → APR 21 35178
 EST. WGT. 1080 LBS.

OK
KP

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-907-D (E)	EWK 12/12/77
Alternate	DCG 12/14/77
TYPED BY	
ry 3/1/78	
MAKING NOTES	

REMARKS

Total Wgt. 3480#

NAME: KROLOR® YELLOW - MEDIUM

NON-BLEEDING

INSTRUCTIONS					-PRESSING-		RECORD				
VAT					262	PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE					4/2/80	STARTED	2:40				
TIME					3:55 PM	CAKES USED	40				
RELEASED BY					(Signature)	WATER ON	6:30 AM				
PRESS	2	22	23	24	45	HRS. WASHED	5				
NO. OF CAKES	46	46	46	52	40	OHMS	2602				
PRESS with					AGITATION	HRS. WASHED					
WASH TO 2000					OHMS with 135-145°F water	OHMS					
TEST AFTER 2					HOURS	HRS. WASHED					
LOAD on 6 cars						OHMS					
						CAKE CONDITION	4				
						NO. CARS LOADED					
						EXPLAIN LOSSES					

SAMPLES 8oz Jar
 DELIVER TO CML for color
 SAMPLED BY 472 RELEASED BY 472 sign for AC.

-DRYING-

DRY 24 HOURS AT 180 °F
 LUMP: - OK - WET - SALTS - CONTAMINATED
 Dry on first stage only.
 NO RECORD OF ANY PROCESSING LOSS
 Reset every 5 hrs til dry.
 ADDITIONAL DRYING HOURS REQUIRED

SAMPLES NO. DRUMS 11
 DELIVER TO NO. CARS PULLED LUMP WGT. 3380
 SAMPLED BY RELEASED BY BLH

-GRINDING-

MILL 939 HSP 1/8" RP SCREEN 3500 RPM
 SCREEN RPM
 MAX. TEMP. 170 °F MAX. TEMP. °F
 EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING DATE MIXED
 SAMPLES 1 ENV & 1 PT can
 DELIVER TO C T L SAMPLED BY RELEASED BY

N32478.01

DUP050461424

35178
4100
18

0.00 *

3.44 +

0.14 -

3.57 +

0.14 -

3.47 +

0.14 -

3.46 +

0.14 -

3.47 +

0.14 -

3.29 +

0.14 -

3.52 +

0.14 -

3.32 +

0.14 -

3.40 +

0.14 -

3.02 +

0.14 -

1.38 +

0.14 -

- 33.80 *

N32478.02

DUP050461425