

91
241

CG 01 CODE YE-735-D PKG.

EST. WGT. 4021

PKG.

LBS.

MAY -0-81-1058

1058

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
YE-735-D (K)	JHK
	DCG 4-19-78
TYPED BY	
MAKING NOTES	
REMARKS	

NAME:

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

YAT					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE					STARTED	8 AM				
TIME					CAKES USED	242				
RELEASED BY					WATER ON	9 PP				
PRESS	2	91			HRS. WASHED	10				
NO. OF CAKES	32	42			OHMS	3570				
PRESS WITH					HRS. WASHED					
WASH TO 3500					OHMS					
TEST AFTER 2					HRS. WASHED					
LOAD ON 5 CARS					OHMS					
					CAKE CONDITION					
					NO. CARS LOADED	5				
					EXPLAIN LOSSES					

STOP AGITATOR AT ABOUT 50"

DO NOT EXTRUDE

SAMPLES

DELIVER TO

SAMPLED BY

RELEASED BY

-DRYING-

12 HRS AT 240°F	LUMP: - OK - WET - SALTS - CONTAMINATE
	ADDITIONAL DRYING HOURS REQUIRED
SAMPLES	NO. CARS PULLED
DELIVER TO	SAMPLED BY
	LUMP WGT. 3971
	RELEASED BY

-GRINDING-

MIKROATOMIZE	MAGNETIC READING ON ATOMIZER PANEL
	BOARD (1.0")
SET ROOF GATE AT 5 INCHES AIR FLOW	
	EXPLAIN LOSSES
SAMPLE / WITHOUT MIXING	DATE MIXED
SAMPLES 1 ENV & 2 PT CANS	
DELIVER TO C T L	SAMPLED BY
	RELEASED BY

DUP050095974

YE-735

58

5

0.00 *
3.73 +
0.12 -
3.61 +
0.12 -
3.56 +
0.12 -
3.57 +
0.12 -
3.75 +
0.12 -
3.86 +
0.12 -
3.83 +
0.12 -
3.41 +
0.12 -
3.52 +
0.12 -
3.64 +
0.12 -
3.66 +
0.12 -
1.01 +
0.12 -
39.71 *