

CODE		LOT		
NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
50	67	3100		
STUMP		Lump	3148	
TOTAL NET WT.	3100	Pkg. N-CODE	1000	
PROD. SPVR.	DATE	WHSE. OPER.		
	3/13/81			

92
245

CG 01 CODE YC-16-B PKG. 93
→ MAY -0.81-E-1230
EST. WGT. 3130 LBS.

OK
AP

PROCESSING INSTRUCTIONS: BATCH UNIT

(A) YC-16-B	PROCESSES	APPROVED BY
	YC-16-B	AJC 4-7-75
		JFH 5-5-75
		DCG 5-4-75
TYPED BY		
MAKING NOTES		
REMARKS		

NAME: MOLYBDATE ORANGE

NON-BLEEDING

INSTRUCTIONS						-PRESSING-		RECORD				
AT	245					PRESSLOAD		1ST	2ND	3RD	4TH	5TH
ATE	5-7					STARTED		10:30 AM				
IME	9:45 PM					CAKES USED		32				
RELEASED BY	237					WATER ON		1 PM				
RESS	91	92	93	2	25	HRS. WASHED		4				
NO. OF CAKES	42	32	32	32	32	OHMS		2000				
PRESS						HRS. WASHED						
WASH TO	2000					OHMS						
TEST AFTER	2					HRS. WASHED						
LOAD ON 4 CARS						OHMS						
						CAKE CONDITION		5				
						NO. CARS LOADED						
						EXPLAIN LOSSES						

SAMPLES
DELIVER TO BLL SAMPLED BY AP RELEASED BY AP

-DRYING-

DRY	16 HOURS AT	220 F	LUMP: - OK - WET - SALTS - CONTAMINATE
			DRYER SECTIONS USED:
			ADDITIONAL DRYING HOURS REQUIRED
			NO. DRUMS 11
SAMPLES			NO. CARS PULLED
DELIVER TO			LUMP WGT 3148
			SAMPLED BY
			RELEASED BY <u>AP</u>

-GRINDING-

MICROATOMIZE	SCREEN	RPM
SET ROOF GATE AT 5 INCHES AIR FLOW	MAX. TEMP.	° F
MAGNETIC READING ON ATOMIZER PANEL 1.0"		
	EXPLAIN LOSSES	
SAMPLE WITHOUT MIXING	DATE MIXED	
SAMPLES 1 ENV		
DELIVER TO C T L	SAMPLED BY	RELEASED BY