FORMULA RECORD

A135 7-41 51162

Exp. No. ____ Date 1-13-42 Class ____ Rex. No. 792

Name Dura-mix House Paint French Gray Card No. 7 See No. ____

POUNDS	GALLONS	MATERIAL NO.
106		414
44		1140 or 18
300		4613
195		3
147		8
579		(2)
1146		Paste Wt.
21		(31)
66		(2281)
3		(152)
70		(348)
16		(12)
4		(CB)
11		12B Basp
		( )
		( )
		( )
		( )
		( )

Customer Trade in General

To Match Standard

Reason for Revision To replace 1538 and to conserve 1526

Viscosity "Z" 75deg. #3 at ____ hrs. after grind

Viscosity ____ at ____ hrs. after grind

Wt./Gal. 4.36

Baume ____

Std. of Fineness 3P

Normal Output 100

Est. Mfg. Loss 2%

Department ____

Parallel No's ____

Label Analysis Checked-Date ____

Label: No Red ☐; Red ☐

New Std. Sample Required No

Date Rec'd ____

Mill ____

Lbs. or Gals. per hour ____

Approved

Formulator CW

Supt. ALG

MANUFACTURING INSTRUCTIONS:

Application: Surface Building **No. Coats** 1 & 2

Undercoater Used **No. Coats**

Method 1 Brush

Reduction: Amount **Reducer Used**

Method 2

Reduction: Amount **Reducer Used**

Drying Time: Touch 6Hrs **Recoat** 4-5days **Stencil**

Hard **Sand** **Handle**

Tack Free **Rub** **Wrap**

Baking Time and Temp.

Gloss Oil **Film** Hard & Tough

Special Tests

8-4-15-4c

DATE	SLIP No.	AMOUNT

FACTORY		FORMULA	SPEC. CARD
Exec. Cost Dept.		4-15-4c	
Cleveland	A	"	
Kensington	C	"	4-15-4c
Allied Research		"	
Kens. Tech. Serv.		"	
Kens. Lacquer			
Newark	N	"	
Oakland	O	"	
M. Senour	M	"	
Detroit	D	"	
Los Angeles	P	"	
Dallas	T	"	
Dayton	B	"	
Gibbsboro	F	"	
Pittsburgh	H		
Cuba	V	"	
Montreal		"	
Buenos Aires	Z	"	
Brazil		"	

I-5 Plan