LOT MAY -0-81- E1501

EST'D WGT 3371

TOTAL EST'D WGT= LBS (CRT ENTRY)

ALTERNATE
TYPED BY JMH

MAKING NOTES

JOB NAME: 01YE698DPR

= PRESSING =

INSTRUCTIONS				
VAT		241		
DATE		5-20		
TIME		1030		
RELEASED BY				
PRESS	2	91	92	93
NO.OF CAKES	32	42	32	32

PRESS WITH AGITATION
WASH TO 2000 OHMS 35-74 F WATER
TEST AFTER 2 HOURS
LOAD ON 4 CARS

RECORD	1ST	2ND	3RD	4TH	5TH
PRESSLOAD					
STARTED	1130				
CAKES USED	46				
WATER ON	0930				
HRS. WASHED	2,30				
OHMS	2000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO CARS LOADED	5				

EXPLAIN LOSSES

SAMPLES
DELIVER TO FDJ

SAMPLED BY
RELEASED BY

= DRYING =

(EXTRUDED) DRY 12 HOURS AT 240 DEG F
(NOT EXTRUDED) DRY 14 HOURS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 1 ENV
DELIVER TO CTL

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS 11
LUMP WGT 3353

= GRINDING =

MILL MIKROATOMIZE SCREEN RPM
MAX. TEMP DEG F
SET ROOF BLAST GATE AT "9" FOR HIGH AIR FLOW

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 ENV
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

1501
41
231

0.00 *

3.03 +
0.14 -/
3.14 +
0.14 -/
3.11 +
0.14 -/
3.33 +
0.14 -/
3.34 +
0.14 -/
3.32 +
0.14 -/
3.25 +
0.14 -/
3.42 +
0.14 -/
3.32 +
0.14 -/
3.31 +
0.14 -/
2.50 +
0.14 -/
33.53 *