MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE Ky 787 LOT 37213

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
50	117	585.0		
	~~STUMP~~ Lump - 5,800			

TOTAL NET WT. _____ PKG. N—CODE 1000

PROD. SPVR.	DATE	WHSE. OPER.
[illegible]	10,8,80	

N35011

95/262

CG 03 CODE KY-787-D PKG. ____

→ SEP·24·80 37213

EST. WGT. 1921 LBS.

OK

TOTAL WGT ~~6121~~ 5845# (REQ ____)

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-787-D (S)	EWK 10-19-77
Alternate	DCG 10-25-77
TYPED BY	
JLC 11-4-77	

MAKING NOTES

REMARKS

NAME: KROLOR® YELLOW-MEDIUM

NON-BLEEDING

-PRESSING-

INSTRUCTIONS						RECORD					
VAT			262			PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE			9-25-80			STARTED	6 PM				
TIME			2:00 PM			CAKES USED	72				
RELEASED BY			[illegible]			WATER ON	10 PM				
PRESS	~~96~~	96	95			HRS. WASHED	1:00 AM				
NO. OF CAKES	~~70~~	72	72			OHMS	3				
PRESS WITH		AGITATION				HRS. WASHED	2000				
WASH TO 2000		OHMS WITH 35-75°F WATER				OHMS					
TEST AFTER 4		HOURS				HRS. WASHED					
LOAD ON 10 CARS						OHMS					
						CAKE CONDITION					
						NO. CARS LOADED	7+3				
TDS						EXPLAIN LOSSES					

SAMPLES 1-8 oz. JAR

DELIVER TO CTL FOR COLOR

SAMPLED BY #469 RELEASED BY A.K

-DRYING-

DRY 12 HRS AT 220°F.
THEN DRY 8 HRS AT 160°F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

No. Drums: 28

SAMPLES

DELIVER TO

NO. CARS PULLED

SAMPLED BY

LUMP WGT. 5800

RELEASED BY BLL

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM

MAX. TEMP. 150°F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING

SAMPLES 1 env + 1 Pt Can

DELIVER TO C T L

DATE MIXED

SAMPLED BY RELEASED BY

DUP050106172

37213
41
348

28
DRUMS

DUP050106173