

CLIVELAND

May 17th, 1929

MR. A. D. JOYCE

IMPROVED PROCIAL WHITE LEAD
Barrel marked - 41193

cc - D.P. Joyce.

Dear Mr. Joyce:-

We have tested out the barrel of 41193 White Lead sent us from the Huston Lead Company, and we find color a trifle yellower than regular Huston White Lead; tint 10% stronger; Oil absorption equal; Residue on the 325 mesh sieve .1%.

In making this into a paint and comparing it with regular Huston Lead, we find it to be stronger in covering properties, equaling the 10% shown on the tinting strength test.

When compared with Anacanda White Lead it does not give as much body to the paint and does not cover as well. The paint made with the 41193 White Lead flows out better and does not show brush marks like the paint made with Anacanda Lead.

This new lead is quite an improvement over our regular material and suggest we have enough sent in to run some large batches of paint in the factory.

Yours very truly,

Technical Director.

JPD:LM

N16999