

PACO TEXTURES MEMO

TO: Wayne Harp

FROM: Doug Merrill

January 8, 1976

SUBJECT: NON ASBESTOS V-100 CEILING TEXTURE

I have received your sample of V-100 with the asbestos left out. To this sample I added 3.3% 7M05 asbestos to simulate your standard.

It appears that this standard can be duplicated by adding 12 pounds of SWP E-790 and 20 pounds of bentonite, to your 3000 pound batch.

On the next available truck I am sending you 20 pounds of SWP E-790 which is 60% solids and 40% water. Therefore, it takes 20 pounds to get 12 pounds of fiber. The cost on this material will be .60 per pound F.O.B., San Carlos.

Please prepare a batch of V-100, leaving the asbestos out and adding 20 pounds of SWP E-790 and 20 pounds of bentonite.

This product may be slightly whiter than your standard.

DWM
DWM/jlb

cc: Bill Harrison
Bob Miller

KM BB 5455