April 25, 1962
Supersedes Formula No. TEX-962
Dated 7/1/57

ACME, TEXAS PLANT FORMULA

PATCHING PLASTER TEX-962

KIND OF PLASTER — Patching Plaster Special

	Maximum	Minimum	Average
SETTING TIME (Tested No. 2)	8 hours	6 hours	7 hours
-/ **TESTING CONSISTENCY** (Tested Neat)	57	55	56
PLASTICITY NUMBER (Tested Neat)	3½	2½	3.0

FORMULA	**Batch**	**Percent**	**Ton**
Stucco No. TEX-38	550.0000 lbs.	53.8390	1076.780 lbs.
Stucco No. TEX-50	450.0000 lbs.	44.0510	881.020 lbs.
Asbestos 7 M	20.0000 lbs.	1.9574	39.148 lbs.
Retarder	1.5625 lbs.	.1526	3.052 lbs.
	1021.5625 lbs.	100.0000	2000.000 lbs.

REMARKS — This formula developed as a dual purpose plaster to be used for both patching and finishing. Is now being sold to the Zinger Handy Patching Plaster Co. at Philadelphia but may be sold with any desired set to other customers, as required.

PATENT DATA — None

-/ Denotes change

JCH/as

PLAINTIFF'S EXHIBIT
GP-1282

SGP 0017263

April 25, 1962
Supersedes Formula No. TEX-962
Dated 7/1/57

ACME, TEXAS PLANT FORMULA

PATCHING PLASTER TEX-962

KIND OF PLASTER	Patching Plaster Special		
SETTING TIME (Tested Neat)	Maximum	Minimum	Average
	8 hours	6 hours	7 hours
-/ TESTING CONSISTENCY (Tested Neat)	57	55	56
PLASTICITY NUMBER (Tested Neat)	3½	2½	3.0

FORMULA	Batch	Percent	Ton
Stucco No. TEX-38	550.0000 lbs.	53.8390	1076.780 lbs.
Stucco No. TEX-50	450.0000 lbs.	44.0510	881.020 lbs.
Asbestos 7 M	20.0000 lbs.	1.9574	39.148 lbs.
Retarder	1.5625 lbs.	.1523	3.052 lbs.
	1021.5625 lbs.	100.0000	2000.000 lbs.

REMARKS: This formula developed as a dual purpose plaster to be used for both patching and finishing. Is now being sold to the Zinger Handy Patching Plaster Co. at Philadelphia but may be sold with any desired set to other customers, as required.

PATENT DATA: None

-/ Denotes change

JGH/as

SGP 0017264

ACME FORMULA #962
ASBESTOS CONTAINING PRODUCTS

SGP 0017261

ACME FORMULA # 962
ASBESTOS CONTAINING PRODUCTS