

TRADE NAME: QUE BRUSHING WHITE FLAT
CATEGORY: III

COLOR: WHITE
QUALITY: 2

PERCENT: 67.8 ; LBS. GAL. YIELD UNIT COST TOTAL COST

Lithopone	200	5.58	4.25	Cwt.	8.50
Titanox C	300	11.49	5.50	"	16.50
Asbestina	200	8.42	1.03	"	2.06
Barytes	200	5.40	1.45-3/4	"	2.92
Whiting	100	4.43	.764	"	.77
XX Zinc Oxide	20	.43	7.25		1.45
Alumina Hydrate	6	.29	15.00	"	.90
VEHICLE 32.2					
#90	6	.60	7.50	"	.45
Stearate Jelly	14	2.00	3.28	"	.46
#21-R	219	30.0	.83	Gal.	24.90
#1062	61	8.0	1.07	"	8.56
Versol	177	27.0	.104	"	2.77
#17	8	1.0	.50	"	.50

CALCULATED YIELD 1,511 104.64 70.74

MANUFACTURED LOSS 3.4%

ACTUAL YIELD 101 Gals.

COST ANALYSIS:
MATERIAL COST PER GAL. OR LB. (TOTAL COST DIVIDED BY ACTUAL YIELD).....7004
DIRECT LABOR COST PER GAL. OR LB.0635
FACTORY OVERHEAD PER GAL. OR LB.0631
BULK COST PER GAL. OR LB.8270
OVERHEADS (CONTAINER PLUS FILLING EXPENSE).....1369
FACTORY TOTAL PER GAL. OR LB.9639

PRICES

THE UNIT PRICE WHICH WAS CHARGED OR WHICH WOULD HAVE BEEN CHARGED IN JANUARY 1942, TO EACH OF THE FOLLOWING TYPES OF BUYERS OR TRANSFERREES:

(A) TO A WHOLESALE COMPANY OR CONTROLLED OUTLET	1.20
(B) TO AN INDEPENDENT WHOLESALE	1.20
(C) TO A WHOLESALE COMPANY OUTLET TO RETAIL CUSTOMER	2.25
(D) TO AN INDEPENDENT RETAILER (DEALER)	1.50
(E) TO OTHER (SPECIFY) Painting Contractor.	1.67

OPA 000946

N 4838