Lacquer Thinner	C-6116
High Test Amyl Acetate	3.8%
Butyl Acetate	11.5%
Isopropyl Acetate	22.4%
Butyl Alcohol	10.6%
Toluene	41.5%
Commercial Xylol	10.2%
	100.0%

Lacquer Thinner	C-4389
Isopropyl Acetate	9.7%
Butyl Acetate	13.7%
High Test Amyl Acetate	4.0%
Denatured Alcohol	8.9%
Butyl Alcohol	4.0%
Toluene	33.7%
Troluoil	26.0%
	100.0%

Enamel Thinner	C-10460
Toluene	100.0%

KE 0016853