

INTER-OFFICE MEMO **TENNECO CHEMICALS, INC.**

TO H. B. Carr AT Burlington DATE July 3, 1969
 FROM E. L. Kanyok AT Burlington COPY TO J. C. Fisher
 SUBJECT Anti-Stat Evaluation File
 Project No.: 30-004

In an effort to try and find a better anti-stat for particle size testing, a series of tests were run using graphite, methanol, ninol, anti-static spray and water.

The following are the results of these tests:

<u>Lot No.</u>	<u>Anti-Stat</u>	<u>40</u>	<u>60</u>	<u>80</u>	<u>100</u>	<u>140</u>	<u>200</u>	<u>Thru</u>
619136	5 gr Graphite	-	1	6	30	77	95	5
619136	5 gr Graphite	-	1	8	33	79	95	5
619136	5 ml Methanol	-	3	9	44	83	95	5
619136	2 ml Methanol	-	1	6	40	83	94	6
619136	0.5 m. Ninol	-	1	8	48	86	96	4
619136	Anti-static spray	-	Tr	6	44	82	92	8
619136	D.M. Water	-	73	77	80	92	96	4

E. L. Kanyok
 E. L. Kanyok

ELK/rjl