MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE RY 907 LOT 3511S

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
1705	1	T- 1#		
1662	1	T- 1#		
STUMP				

TOTAL NET WT. 3361 PKG. N-CODE

PROD. SPVR.	DATE	WHSE. OPER.
	7/21/	

N 2624

95

240

CG 03 CODE KY-907-D PKG. ____

→ MAR 28 35115

EST. WGT. 1080 LBS.

OK

KP

PROCESSING INSTRUCTIONS: BATCH UNIT

	PROCESSES	APPROVED BY
	KY-907-D (D)	EWK 12/12/77
		DCG 12/13/77
	TYPED BY	
	rj 2/6/78	

MAKING NOTES

REMARKS

TOTAL WGT. 3480#

NAME: KROLOR® YELLOW - MEDIUM **NON-BLEEDING**

INSTRUCTIONS -PRESSING- RECORD

VAT			240		
DATE			3-28		
TIME			6:15		
RELEASED BY			[illegible]		
PRESS	2	22	23	24	
NO. OF CAKES	46	46	46	52	

PRESS with AGITATION

WASH TO 2000 OHMS with 135-145°F water

TEST AFTER 2 HOURS

LOAD on 6 cars

SAMPLES 8oz Jar

DELIVER TO CTL for Color

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	10:30 AM				
CAKES USED	46				
WATER ON	9PM				
HRS. WASHED	8				
OHMS	2000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	6				

EXPLAIN LOSSES

SAMPLED BY 169 RELEASED BY JDS

-DRYING-

DRY 24 HOURS AT 180 °F

Dry on first stage only.

Reset EVERY 5 hrs til dry.

SAMPLES

DELIVER TO

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 12

NO. CARS PULLED LUMP WGT 7840

SAMPLED BY RELEASED BY

-GRINDING-

MILL 939 HSP 1/8"RP SCREEN 3500 RPM

MAX. TEMP. 170°F

SAMPLE / / WITHOUT MIXING

SAMPLES 1 ENV & 1 PTCAN

DELIVER TO CTL

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

DATE MIXED

SAMPLED BY RELEASED BY

N 26246.01

DUP050093556

17. DRUMS
DUMP-6-OHMS-

35	1.15 #
	1.24 #
	.41 #
	3.11
	.14 -
	2.95
	.14 -
	2.94
	.14 -
	3.25
	.14 -
	3.06
	.14 -
	3.31
	.14 -
	2.96
	.14 -
	3.03
	.14 -
	2.90
	.14 -
	2.89
	.14 -
	2.96
	.14 -
	1.96
	.14 -
33	6.64 T