

TEXT FOR FOREIGN FILING

Our Reference: CH-1371 JACOBSON

Applicant's Name: E. I. DU PONT DE NEMOURS AND COMPANY

Title: TITANIUM DIOXIDE PIGMENT COATED WITH CERIUM
CATIONS, SELECTED ACID ANIONS, AND ALUMINA

Convention Priority:

<u>U.S. Serial No.</u>	<u>Filed</u>	<u>Inventors</u>	<u>Our Reference</u>
857,325	April 30, 1986	Jacobson	CH-1371

Inventor Details

Howard Wayne JACOBSON

2009 Longcome Drive
Wilmington, Delaware 19810

USA Citizen
Research Fellow for Du Pont Company

Miscellaneous

(Abstract, Prior Art, Related Cases, Commercial Significance, if needed.)

N 30939

TITLE

5 Titanium Dioxide Pigment
Coated with Cerium Cations,
Selected Acid Anions, and Alumina

BACKGROUND OF THE INVENTION

10 The present invention relates generally to
pigments composed of coated TiO_2 particles, and
particularly to TiO_2 pigments having coatings comprising
cerium cations, selected acid anions, and an outer
coating of alumina.

15 TiO_2 has a high refractive index for its
density, which renders it a superior pigment for use in
coatings, e.g., paints. However, TiO_2 is photoactive;
exposure to ultraviolet radiation results in generation
of free radicals on the surface of TiO_2 particles.
Thus, where a TiO_2 pigment is employed in a paint
exposed to sunlight, free radicals are generated which
20 can migrate to the film-forming component of the paint,
resulting in coating degradation or failure.

Therefore, minimizing free radical migration
is desirable in order to provide lightfast and stable
pigments for coating use. Heretofore, the majority of
25 commercial TiO_2 pigments have been coated with dense
silica or densified alumina to provide lightfastness.
However, some patent references have disclosed use of
cerium in association with TiO_2 pigments to promote
lightfastness.

30 Lederer, U. S. Patent 3,513,007, discloses
 TiO_2 particles having coatings formed from dispersions
containing water-soluble hydrolyzable compounds of
silicon, titanium, zirconium, or phosphorus, to which
water-soluble hydrolyzable compounds of aluminum,
cerium, and or calcium and alkali are added.
35

Barnard, U. S. Patent 4,239,548, discloses pigments having inner coatings comprising cerium and phosphate radicals and outer coatings comprising aluminum and phosphate radicals and optionally hydrous alumina.

Jacobson, U. S. Patent 4,460,655, describes pigments of TiO_2 particles associated with compounds selected from the group consisting of $\text{Na}_7\text{Ce}_6\text{F}_{31}$, $\text{K}_7\text{Ce}_6\text{F}_{31}$, $\text{Li}_7\text{Ce}_6\text{F}_{31}$, and $(\text{NH}_4)_7\text{Ce}_6\text{F}_{31}$.

Jacobson, U. S. Patent 4,461,810, discloses pigments of TiO_2 particles, the surfaces of which are associated with cerium cations and sulfate, phosphate, or silicate anions. The particles are also provided with an outer coating of alumina.

Newland et al., U. S. Patent 4,022,632, describes TiO_2 pigments treated with carboxylate salts of cobalt, cerium, or manganese.

Bramekamp, U. S. Patent 3,506,466, discloses TiO_2 pigment particles coated with inorganic oxides, where the inorganic oxide bears on its surface an amine salt of an oxycarboxylic acid selected from the group consisting of lactic, citric, malic, tartaric, and glycolic acids.

It has now been found that pigments of TiO_2 particles treated with cerium cations in association with certain polyfunctional water-soluble acid anions or borate ions, and then topcoated with alumina, exhibit excellent lightfastness, gloss, and dispersion characteristics.

SUMMARY OF THE INVENTION

The present invention provides a pigment consisting essentially of rutile TiO_2 particles bearing coatings of alumina or alumina-silica, the particle surfaces having associated therewith 0.05-2%, by weight of the TiO_2 , of cerium cations and an associated

quantity of borate anions or polyfunctional organic acid anions having a solubility in water of at least 10 grams per liter at 25°C.

5

DETAILED DESCRIPTION OF THE INVENTION

The pigments of the present invention are composed of rutile TiO_2 particles treated with cerium cations in association with selected polyfunctional organic acid anions such as citrate anions, and then topcoated with alumina or alumina-silica. Optionally, the acid anions can be borate. In extreme lightfastness exposures, the pigments of this invention provide performance equivalent to TiO_2 coated with 6% by weight silica and 2% by weight alumina. It is believed that cerium citrate in association with the TiO_2 particle surfaces provides recombination centers for electron/hole pairs produced when pigments containing such particles are exposed to actinic radiation. Quenching of electron/hole pairs eliminates free radical production which might otherwise degrade a paint film or other organic materials in proximity to pigment particles.

20

The TiO_2 used to prepare the pigment of the invention can be of the conventional rutile variety, prepared by either the chloride or sulfate process.

25

Associated with the particle surfaces of the TiO_2 are cerium cations and selected acid anions. "Associated with the particle surfaces" means that the ions are bound to the TiO_2 particles by a chemical or physical attraction.

30

The acid anions associated with the cerium cations are borate anions or polyfunctional organic acid anions having water solubilities greater than 10 grams per liter at 25°C. Exemplary of such organic acid anions are citrate, succinate, fumarate, adipate, tartrate, and maleate ions. Of the foregoing, citrate ions are preferred.

35

The cerium cations can be supplied by any water-soluble cerium salt, e.g., ceric sulfate or ceric nitrate, which are added to rutile slurries at pH 2-7. Polyfunctional organic acid anions are supplied by addition of the appropriate acid. Borate anions are supplied by addition of $\text{Na}_2\text{B}_2\text{O}_4$. The cerium ion content of the pigment can be determined by ion plasma chromatography. The polyfunctional organic acid anion content can be determined using a Leco or other total carbon analyzer.

The amount of alumina or alumina-silica which the particles bear as coatings can be varied depending primarily upon the pigment's intended use. Ordinarily, the alumina coating will constitute 0.5-10% of the total weight of the particles. Preferably, the alumina coating constitutes 1-6%, and most preferably, 2-4%, of the total weight of the pigment particles. The amount of alumina the particles bear as coatings, expressed as percent by weight, is calculated by first determining, by ion plasma spectroscopy, the alumina content of the coated pigment. The alumina content of the uncoated rutile TiO_2 is similarly determined, and the alumina content attributable to the coating is determined by computing the difference between coated and uncoated alumina contents.

The pigment of the present invention can be prepared from an aqueous slurry containing 200-450 grams per liter TiO_2 . This slurry is brought to 45°-70°C and is held at that temperature throughout the preparation procedure. The slurry is adjusted to a pH at which added cerium ions will remain in solution by addition of mineral acid, e.g., HCl, and then sufficient cerium salt is added to provide a cerium ion concentration in the slurry of 0.05-2%, by weight of the TiO_2 . For example, if cerium ions are supplied by addition of ceric nitrate, pH should be adjusted to 2-4; if cerium ions

are added in the form of ceric sulfate, pH should be adjusted to the range 2-7.

At this point, a sufficient quantity of a selected anion species (i.e., organic acid or borate) is added to the slurry to provide a concentration of added anion ranging from 100% to 300% of the cerium ion concentration. As a result, cerium will precipitate upon the surfaces of the TiO_2 particles in association with the added anion.

Alumina is then precipitated on the TiO_2 particles by slowly adding enough sodium aluminate to the slurry to provide a concentration of about 2-8% by weight of the TiO_2 . Acid, normally sulfuric or hydrochloric, is added at the same time to maintain the pH of the slurry within the range 6-9 during the precipitation step. After addition of aluminate is complete, the slurry is allowed to cure, with continuous stirring, for 15-30 minutes.

The resulting pigment is then separated from the liquid by filtration or centrifugation, washed with water, and dried.

Coating compositions can be prepared with the pigments of the invention in conventional ways, e.g., by blending the pigment with a film-forming component and a liquid carrier.

The following examples illustrate particular aspects of the present invention. In the examples, all parts and percentages are by weight and all degrees are Celsius unless otherwise indicated.

Example 1

In a large plastic vessel equipped with stirring apparatus and a pH probe, 11,000 parts water are mixed with 5000 parts rutile TiO_2 .

The resulting slurry is heated to 60° , and the pH is adjusted to about 3.0 by addition of HCl. 42 parts of a 1.5 M $\text{Ce}(\text{NO}_3)_4$ solution are then added,

followed by 40 parts citric acid. The resulting mixture is then stirred for a period of about 5 minutes, and then the pH is increased to about 7.5 by addition of NaOH.

5 A coating of 2% hydrous alumina is then deposited on the pigment by simultaneously adding 250 mL NaAlO_2 solution (containing the equivalent of 400 g Al_2O_3 per liter solution) and HCl, such that the pH of the slurry is continuously maintained from about 7.0 to about 7.5.

10 The resulting coated pigment is cured by holding for about 30 minutes at 60° and pH 7.5. The pigment is then filtered from the slurry, washed free of salts with deionized water, and air-dried. The pigment is then micronized, using 3 lbs. superheated steam per lb. pigment. The resulting pigment, containing about 0.2% CeO_2 as $\text{Ce}_3(\text{C}_6\text{H}_5\text{O}_7)_4$, and a 2.0% alumina coating, is suitable for use in paint systems.

20 Example 2

A mill base is made by mixing

Pigment of Example 1	387 parts
alkyd resin	
(Syntex ©3145;	
Celanese Coatings Co.)	149.6 parts
n-butanol	9.4 parts
xylol	79 parts.

30 This mixture is sand ground, and then the sand is filtered from the mill base. A paint is made by mixing 100 parts of the mill base with the following:

35

	xylol	1.4 parts
	alkyd resin	
	(Syntex® 3145;	
5	Celanese Coatings Co.)	71.8 parts
	melamine resin solution	
	(Cymel® 248-8, 55%	
	solids, American	
	Cyanamid Co.)	38.5 parts.

10

15

20

25

30

35

CLAIMS

What is claimed is:

- 5 1. A pigment consisting essentially of rutile
TiO₂ particles bearing coatings of alumina or
alumina-silica, the particle surfaces having associated
therewith 0.05-2%, by weight of the TiO₂, of cerium
cations and an associated quantity of borate anions or
polyfunctional organic acid anions having a a solubility
10 in water of at least 10 grams per liter at 25°C.
2. A pigment according to Claim 1, wherein
the alumina or alumina-silica coating constitutes
0.5-10% of the total weight of the TiO₂ particles.
- 15 3. A pigment according to Claim 2, wherein
the alumina or alumina-silica coating constitutes 1-6%
of the total weight of the TiO₂ particles.
4. A pigment according to Claim 3, wherein
the alumina or alumina-silica coating constitutes 2-4%
of the total weight of the TiO₂ particles.
- 20 5. A pigment according to Claim 1, wherein
the aassociated anions are borate ions.
- 25 6. A pigment according to Claim 1, wherein
the associated anions are polyfunctional organic acid
anions having a a solubility in water of at least 10
grams per liter at 25°C.
- 30 7. A pigment according to Claim 1, wherein
the associated anions are selected from the group
consisting of citrate, succinate, fumarate, adipate,
tartrate, and maleate ions.
- 35

8. A pigment according to Claim 1, wherein the associated anions are citrate ions.

5 9. A pigment according to Claim 2, wherein the associated anions are citrate ions.

10 10. A pigment according to Claim 3, wherein the associated anions are citrate ions.

11. A pigment according to Claim 4, wherein the associated anions are citrate ions.

15 12. A coating composition comprising a pigment according to Claim 1, a film-forming material, and a liquid carrier.

20 13. A coating composition comprising a pigment according to Claim 2, a film-forming material, and a liquid carrier.

14. A coating composition comprising a pigment according to Claim 3, a film-forming material, and a liquid carrier.

25 15. A coating composition comprising a pigment according to Claim 4, a film-forming material, and a liquid carrier.

30 16. A coating composition comprising a pigment according to Claim 5, a film-forming material, and a liquid carrier.

35 17. A coating composition comprising a pigment according to Claim 6, a film-forming material, and a liquid carrier.

18. A coating composition comprising a pigment according to Claim 7, a film-forming material, and a liquid carrier.

5 19. A coating composition comprising a pigment according to Claim 8, a film-forming material, and a liquid carrier.

10 20. A coating composition comprising a pigment according to Claim 9, a film-forming material, and a liquid carrier.

15

20

25

30

35

TITLE

5 Titanium Dioxide Pigment
Coated with Cerium Cations,
Selected Acid Anions, and Alumina

ABSTRACT

10 A pigment consisting essentially of rutile
TiO₂ particles coated with alumina or alumina-silica,
and having particle surfaces associated with cerium
cations and borate anions or water-soluble
polyfunctional organic acid anions, is useful in coating
compositions.

15

20

25

30

35